

Not a Current Stock Product

Please contact our team for assistance.

Pressure-sensitive adhesives

Latex

Latex

Film

1 Mil Polyester TC Clear / AP151 Opaque @ 1.50 Cwt. / AP151 / LPG @ 1.30 Cwt. / 1.5 Mil Clear Polyester L-3 / 1.5 MIL CLEAR PET LINER L-3C

FACESTOCK

This facestock displays high clarity and good UV resistance. The versatile topcoating is compatible with solvent base, water based and UV curable inks and can also perform well when used in silk screen or offset print processes.

Type

Film

Tensile MD

28000 Psi

Tensile CD

34000 Psi

Elong MD

300

Elong CD

110

PROPERTIES

VALUE

Caliper

1.00 Mil

REGULATORY APPROVAL

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

FSC

No

*Please contact your sales representative for details

ADHESIVE

An outstanding general purpose permanent opaque adhesive that has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting and stripping traits. Provides opacity for cover up applications.

Type

Permanent

Composition

Latex

Shear

0

Min. Application Temperature

35 F

Min. Service Temperature

-64 F

Max. Application Temperature

220 F

PROPERTIES

VALUE

Stainless Steel

7.3 lbs/linear in.

Glass	5,7 lbs/linear in.
Polyethylene	6.5
Painted Metal	7.0 lbs/linear in.

REGULATORY APPROVAL

RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

ADHESIVE

An outstanding general purpose permanent adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing & can be used on many different substrates. Displays excellent die-cutting & stripping traits.

Type Permanent	Composition Latex	Shear 80
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 220 F

PROPERTIES	VALUE
------------	-------

Stainless Steel	7.3 lbs/linear in.
Glass	5,7 lbs/linear in.
Polyethylene	6.5
Corrugated	2.50 lbs./in.
Painted Metal	7.0 lbs/linear in.
Loop Tack	5.00 oz/in ²

REGULATORY APPROVAL

RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

LINER

A 1.5 mil polyester liner which has been silicone coated one side to give a controlled release. It has extremely high internal strength for ease in manufacturing, converting and end-usage, making it an outstanding liner for high speed, automatic applications.

Tensile MD 33000	Tensile CD 0
Tear MD	Tear CD

0	0	
DESCRIPTION	VALUE	
Basis Weight	0	
Caliper	1,5	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	
*Please contact your sales representative for details		

LINER		
A 1.5 Mil clear pet liner which is silicone coated one side to give a controlled release. Uniform caliper and high internal strength enhance the excellent die-cutting characteristics of this liner.		
Type 17617		
Tensile MD 32000	Tensile CD 0	
Tear MD 0	Tear CD 0	
DESCRIPTION	VALUE	
Caliper	1.5	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

orders.us@beontag.com