

## Not a Current Stock Product

Please contact our team for assistance.

Pressure-sensitive adhesives

Hot Melt

Film

# 10 Mil Synthetic Paper / AP151 @ 1.0 Cwt. / 40#SCK LINER L-2

### Facestock

A matte white reinforced polypropylene film suitable for a wide range of applications where durability, strength, moisture, chemical resistance and superb printability (including thermal transfer) are required. FDA compliant.

#### Type

Film

#### Tensile MD

4000 Psi

#### Tensile CD

2500 Psi

#### Tear MD

550 Grams

#### Tear CD

630 Grams

#### Elong CD

82

#### Properties

#### Value

#### Caliper

10.00 Mil

#### Opacity

91

### Regulatory Approval

#### RoHS

Yes

#### Prop65

Yes

#### REACH

Yes

#### TPCH

Yes

#### CPSIA

Yes

#### UL

No

#### FSC

No

\*Please contact your sales representative for details

### Adhesive

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

#### Type

#### Composition

#### Shear

Permanent	Hot Melt	80
<b>Min. Application Temperature</b> 35 F	<b>Min. Service Temperature</b> -65 F	<b>Max. Application Temperature</b> 220 F

Properties	Value
<b>Stainless Steel</b>	7.3 lbs/linear in.
<b>Glass</b>	5.7
<b>Polyethylene</b>	6.5
<b>Corrugated</b>	2.50 lbs./in.
<b>Painted Metal</b>	7.0 lbs/linear in.
<b>Loop Tack</b>	5.00 lbs./in <sup>2</sup>

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No	<b>Indirect Food</b> Yes	

\*Please contact your sales representative for details

### Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

**Type**  
5517542

<b>Tensile MD</b> 34 Lbs/In	<b>Tensile CD</b> 22 Lbs/In
<b>Tear MD</b> 32 Grams	<b>Tear CD</b> 34 Grams

Description	Value
<b>Basis Weight</b>	40 Lbs/Rm
<b>Caliper</b>	2.5 Mil

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No

**Direct Food**

No

\*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

## ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)[orders.us@beontag.com](mailto:orders.us@beontag.com)