

Not a Current Stock Product

Please contact our team for assistance.

- Pressure-sensitive adhesives
- Acrylic
- Film

2.6 Mil Label Lyte / AT150 / LPG @ 1.80 Cwt. / 50#SCK L-3

FACESTOCK

A 2.6 mil heat set, biaxially oriented multi-layer white polypropylene film. It is designed for excellent opacity and has a high surface treatment for good ink adhesion while maintaining its pearlescent look.

Type
Film

Tensile MD
13000 Psi

Tensile CD
25000 Psi

Elong MD
100

Elong CD
50

PROPERTIES

VALUE

Caliper

2.60 Mil

Opacity

88

REGULATORY APPROVAL

Prop65
Yes

FSC
No

*Please contact your sales representative for details

ADHESIVE

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Excellent permanency at room temps. Very good plasticizer, UV and solvent resistance. This adhesive offers a neutral pH level (Acid Free)

Type
Permanent

Composition
Acrylic

Shear
105

Min. Application Temperature
-20 F

Min. Service Temperature
-65 F

Max. Application Temperature
160 F

PROPERTIES

VALUE

Stainless Steel

5.4 lbs/linear in.

Glass

4.4

Polyethylene

4.2

Corrugated

1.50 lbs./in.

Painted Metal

5.2 lbs/linear in.

Loop Tack

3.00 lbs./in2

REGULATORY APPROVAL**RoHS**
Yes**Prop65**
No**REACH**
Yes**TPCH**
Yes**CPSIA**
Yes**UL**
No**Direct Food**
No**Indirect Food**
Yes

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type
5517353**Tensile MD**
40**Tensile CD**
24**Tear MD**
44**Tear CD**
48**DESCRIPTION****VALUE****Basis Weight**

50

Caliper

3.2

REGULATORY APPROVAL**RoHS**
Yes**Prop65**
Yes**REACH**
Yes**TPCH**
Yes**CPSIA**
Yes**UL**
No**Direct Food**
No

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426

800-358-4448

orders.us@beontag.com