

# Not a Current Stock Product

Please contact our team for assistance.

- Pressure-sensitive adhesives
- Acrylic
- Film

## 3.2 mil White DT TC BOPP / ALL TEMP / 2.5 mil SCK L-3

FACESTOCK

Facestock(3.2 mil White DT TC BOPP): A white direct thermal topcoated, biaxially oriented (BOPP) film that may be used in a wide variety of pressure sensitive label applications. The solid white polypropylene core is treated one side with a print receptive gloss coating for superb ink adhesion, and has great stiffness for efficient dispensability.

Type

Film

Tensile MD

11500 psi

Tensile CD

28000 psi

Elong MD

179

Elong CD

43

PROPERTIES

VALUE

Caliper

3.2 mil

REGULATORY APPROVAL

RoHS

Yes

TPCH

Yes

FSC

No

Prop65

No

CPSIA

Yes

REACH

Yes

UL

No

\*Please contact your sales representative for details

ADHESIVE

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Excellent permanency at room temperatures. Very good plasticizer, UV and solvent resistance. This adhesive offers a neutral ph level (Acid Free)

Type

Permanent

Composition

Acrylic

Shear

100

Min. Application Temperature

-20 F

Min. Service Temperature

-65 F

Max. Application Temperature

160 F

PROPERTIES

VALUE

Stainless Steel

5.1 lbs/linear in.

Glass

4,4 lbs/linear in.

<b>Polyethylene</b>	4.2	
<b>Corrugated</b>	1.50 lbs./in.	
<b>Painted Metal</b>	4.9 lbs/linear in.	
<b>Loop Tack</b>	2.90 oz/in <sup>2</sup>	
<b>REGULATORY APPROVAL</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>Direct Food</b> Yes
<b>Indirect Food</b> Yes		
*Please contact your sales representative for details		

<b>LINER</b>		
Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a hard smooth caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
<b>Type</b> 18360		
<b>Tensile MD</b> 35	<b>Tensile CD</b> 16	
<b>Tear MD</b> 42	<b>Tear CD</b> 46	
<b>DESCRIPTION</b>	<b>VALUE</b>	
<b>Basis Weight</b>	40	
<b>Caliper</b>	2.5	
<b>REGULATORY APPROVAL</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		
*Please contact your sales representative for details		

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:  
 Beontag  
 6206 Wolf Creek Pike  
 Trotwood, OH 45426  
[800-358-4448](tel:800-358-4448)

