

## Not a Current Stock Product

Please contact our team for assistance.

Pressure-sensitive adhesives Latex

# 3.7 Mil Smudgeproof Kimdura(TM) / AP151 / 50#SCK L-3

### **FACESTOCK**

A 3.7 mil white Smudge Kimdura which is a biaxially oriented three ply polypropylene which combines extraordinary edge tear resistance with a smooth, uniform surface that provides brilliant imagery, superior print quality and smudge resistance.

Type Film

**Tensile MD Tensile CD** 24 Lbs/in 18 Lbs/in Tear CD **Tear MD** 26 Grams 15 Grams

**PROPERTIES VALUE** 

Caliper 3.70 Mil

**REGULATORY APPROVAL** 

**RoHS** Prop65 **REACH** Yes Yes Yes **TPCH CPSIA FSC** Yes Yes No

#### **ADHESIVE**

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

Type Composition Shear 80 Permanent Latex

Min. Application Temperature Min. Service Temperature Max. Application Temperature

-65 F 220 F 35 F

**PROPERTIES VALUE** 

Stainless Steel 7.3 lbs/linear in.

5.7 lbs/linear in. Glass

**Polyethylene** 6.5

2.50 lbs./in. Corrugated

<sup>\*</sup>Please contact your sales representative for details

Painted Metal 7.0 lbs/linear in.

**Loop Tack** 5.00 oz/in<sup>2</sup>

**REGULATORY APPROVAL** 

RoHSProp65REACHYesNoYes

TPCH CPSIA Direct Food

Yes Yes Yes

**Indirect Food** 

Yes

\*Please contact your sales representative for details

### **LINER**

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

**Type** 5517353

Tensile MD Tensile CD

40 24

 Tear MD
 Tear CD

 44
 48

DESCRIPTION VALUE

Basis Weight 50

Caliper 3.2

**REGULATORY APPROVAL** 

RoHS<br/>YesProp65<br/>YesREACH<br/>YesTPCH<br/>YesCPSIA<br/>YesUL<br/>No

**Direct Food** 

No

\*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448

orders.us@beontag.com