

Not a Current Stock Product

Please contact our team for assistance.

Pressure-sensitive adhesives Acrylic

3.7 Mil Smudgeproof Kimdura(TM) / TS585WS @ 1.60 Cwt. / 40#SCK L-10 / 50#SCK L-3

FACESTOCK

A 3.7 mil white Smudge Kimdura which is a biaxially oriented three ply polypropylene which combines extraordinary edge tear resistance with a smooth, uniform surface that provides brilliant imagery, superior print quality and smudge resistance.

Туре Film

Tensile MD Tensile CD 24 Lbs/in 18 Lbs/in **Tear MD Tear CD** 26 Grams 15 Grams

PROPERTIES VALUE

3.70 Mil Caliper

REGULATORY APPROVAL

REACH RoHS Prop65 Yes Yes Yes **TPCH CPSIA FSC** Yes Yes No

ADHESIVE

A specialty adhesive designed to adhere to slightly wet surfaces with good ultimate adhesion when applied at temperatures as low as -20 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for hard to label substrates.

Туре	Composition	Shear
Permanent	Acrylic	65

Min. Application Temperature Min. Service Temperature Max. Application Temperature

-20 F -65 F 140 F

PROPERTIES VALUE

Stainless Steel 4.8 lbs/linear in. **Glass** 3,2lbs/linear in. **Polyethylene** 6,5lbs/linear in.

^{*}Please contact your sales representative for details

Corrugated 1.45 lbs./in.

Painted Metal 4.4 lbs/linear in.

Loop Tack 2.70 oz/in²

REGULATORY APPROVAL

RoHSProp65REACHYesNoYes

TPCH CPSIA Direct Food

Yes Yes No

Indirect Food

Yes

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type 17142

 Tensile MD
 Tensile CD

 34 Lbs/In
 22 Lbs/In

 Tear MD
 Tear CD

 32 Grams
 34 Grams

DESCRIPTION VALUE

Basis Weight 40 Lbs/Rm

Caliper 2.5 Mil

REGULATORY APPROVAL

 RoHS
 Prop65
 REACH

 Yes
 Yes
 Yes

 TPCH
 CPSIA
 UL

 Yes
 No

Direct Food

No

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Туре

5517353

Tensile MD Tensile CD

40 24

Tear MD Tear CD

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details

44	48		
DESCRIPTION	VALUE		
Basis Weight	50		
Caliper	3.2		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	UL	
Yes	Yes	No	
Direct Food No			
*Please contact your sales representative for details			

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448 orders.us@beontag.com