## Not a Current Stock Product

Please contact our team for assistance.

Pressure-sensitive adhesives Acrylic

Paper

## 60# Semigloss / TS523 @ 1.70 Cwt. / 4.6 MIL LAYFLAT L-30

<b>FACESTOCK</b> A coated one side semigloss stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 88% Brightness and an 90% opacity.				
<b>Type</b> Paper				
<b>Tensile MD</b> 17 lbs/in				
<b>Tear CD</b> 56 g				
PROPERTIES	VALUE			
Basis Weight	60			
Caliper	3.1			
REGULATORY APPROVAL				
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes		
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No		
FSC No				
*Please contact your sales representative for details				

## ADHESIVE

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

<b>Type</b> Permanent	<b>Composition</b> Acrylic	Shear 350
<b>Min. Application Temperature</b> 35 F	<b>Min. Service Temperature</b> -65 F	<b>Max. Application Temperature</b> 200 F
PROPERTIES	VALUE	
Stainless Steel	6.1 lbs/linear in.	

Polyethylene	2.9	2.9		
Corrugated	1.50 lbs./in. 5.4 lbs/linear in.			
Painted Metal				
Loop Tack	2.70 oz/in <sup>2</sup>	2.70 oz/in <sup>2</sup>		
REGULATORY APPROVAL				
RoHS	Prop65	REACH		
Yes	No	Yes		
ТРСН	CPSIA	Direct Food		
Yes	Yes	No		
Indirect Food				
Yes				
*Please contact your sales representative for details				
riease contact your sales representative for details				

## LINER

A clay coated kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand all diecutting, margin punching, perforating, fanfolding and refolding processes. It is an excellent lay-flat liner.

<b>Туре</b> 917166			
Tensile MD	Tensile CD		
56	24		
Tear MD	Tear CD		
73	69		
DESCRIPTION	VALUE		
Basis Weight	72		
Caliper	4.5		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	UL	
Yes	Yes	No	
Direct Food			
No			
*Please contact your sales representative for details			

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

or for incidental or consequential damages. BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG's standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS: Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 <u>800-358-4448</u> <u>orders.us@beontag.com</u>