

10 PT C1S Tag TP170 4.6 Mil Layflat L-3

ITEM #82424

FACESTOCK

A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers excellent stiffness and high internal strength.

Type

Paper

Tear MD

205 Grams

Tear CD

200 Grams

PROPERTIES

VALUE

Basis Weight

133lbs/3000 sq ft

Caliper

10.00 Mil

Brightness

94

REGULATORY APPROVAL

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

FSC

No

*Please contact your sales representative for details

ADHESIVE

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Type

Permanent

Composition

Acrylic

Shear

300

Min. Application Temperature

35 F

Min. Service Temperature

-65 F

Max. Application Temperature

180 F

PROPERTIES

VALUE

Stainless Steel

5.2 lbs/linear in.

Glass

3,2lbs/linear in.

Polyethylene

1.6

Corrugated

1.40 lbs./in.

Painted Metal

5.2 lbs/linear in.

Loop Tack2.20 oz/in²**REGULATORY APPROVAL****RoHS**
Yes**Prop65**
No**REACH**
Yes**TPCH**
Yes**CPSIA**
Yes**Direct Food**
No**Indirect Food**
Yes

*Please contact your sales representative for details

LINER

A clay coated kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand all diecutting, margin punching, perforating, fanfolding and refolding processes. It is an excellent layflat liner.

Type

719363

Tensile MD

51

Tensile CD

0

Tear MD

0

Tear CD

100

DESCRIPTION**VALUE****Basis Weight**

72

Caliper

4.6

REGULATORY APPROVAL**RoHS**
Yes**Prop65**
Yes**REACH**
Yes**TPCH**
Yes**CPSIA**
Yes**UL**
No**Direct Food**
No

*Please contact your sales representative for details

Last update: 02/11/2025

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG'S plant or at the location of the products (at BEONTAG'S election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426

800-358-4448

orders.us@beontag.com