

Pressure-sensitive adhesives

Acrylic

1.5 MIL CLEAR ACETATE / TS523 @ 1.5 Cwt. / 65#C2S L-3

ITEM #84602

FA	^E	CT	\sim		v
ГΑ	VΕ	ъı	U	u	n

A 1.5 mil matte clear film with excellent ink receptivity and printability.

Туре Film

Tensile MD

Tensile CD 20 Lbs/in 25 Lbs/in

Elong MD 325

PROPERTIES VALUE

Caliper 1.50 Mil

REGULATORY APPROVAL

RoHS Prop65 **REACH** Yes Yes Yes **TPCH CPSIA** UL Yes Yes No

FSC No

ADHESIVE

Glass

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Composition Shear Type Permanent 350 Acrylic

Min. Application Temperature Min. Service Temperature Max. Application Temperature

35 F -65 F 200 F

2,8lbs/linear in.

PROPERTIES VALUE

Stainless Steel 5.6 lbs/linear in.

Polyethylene 2.9

Corrugated 1.50 lbs./in.

Painted Metal 4.9 lbs/linear in.

Loop Tack 2.70 oz/in²

^{*}Please contact your sales representative for details

REGULATORY APPROVAL

RoHSProp65REACHYesNoYes

TPCH CPSIA Direct Food

Yes Yes

Indirect Food

Yes

LINER

A fully bleached kraft liner which has been silicone coated one side to give a controlled release. This paper has high internal strength top withstand all conventional processing operations including die-cutting, perforating, fanfolding and refolding processes.

No

Type 47365

Tensile MDTensile CD33 Lbs/In18 Lbs/InTear MDTear CD51 Grams53 Grams

DESCRIPTION VALUE

Basis Weight 65 Lbs/Rm

Caliper 3.8 Mil

REGULATORY APPROVAL

RoHS
YesProp65
YesREACH
YesTPCH
YesCPSIA
YesUL
No

Direct Food

No

Last update: 05/01/2024

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details