

1.6 MIL WHITE TC BOPP / AT333 @ 1.30 Cwt. / 40#SCK L-3

ITEM #988079

FACESTOCK A white direct thermal topcoated, biaxially oriented (BOPP) film that may be used in a wide variety of pressure sensitive label applications. The solid white polypropylene core is treated one side with a print receptive gloss coating for superb ink adhesion, and has great stiffness for efficient dispensability.		
Type Film		
Tensile MD 12000 Psi	Tensile CD 32000 Psi	
Elong MD 145	Elong CD 45	
PROPERTIES		
Caliper	1.60 Mil	
Opacity	89	
REGULATORY APPROVAL		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	UL No
FSC No		
*Please contact your sales representative for details		

ADHESIVE An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.		
Type Permanent	Composition Acrylic	Shear 60
Min. Application Temperature -20 F	Min. Service Temperature -65 F	Max. Application Temperature 160 F
PROPERTIES	VALUE	
Stainless Steel	4.7 lbs/linear in.	
Glass	1,3lbs/linear in.	
Polyethylene	2.2	
Corrugated	1.40 lbs./in.	

Painted Metal	4.4 lbs/linear in.	
Loop Tack	2.20 oz/in ²	
REGULATORY APPROVAL		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		
*Please contact your sales representative for details		

LINER		
Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type 5517342		
Tensile MD 34	Tensile CD 22	
Tear MD 32	Tear CD 34	
DESCRIPTION		
VALUE		
Basis Weight	40	
Caliper	2.5	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com