

Pressure-sensitive adhesives

Acrylic

Film

2.6 Mil Matte White BOPP P / B TS523 1.5 mil TS523 50#SCK L-3

ITEM #86625

FACESTOCK

A 2.6 Mil matte white C2S, antistatic polypropylene film that is designed for thermal transfer printability. Features excellent print resolution and abrasion resistance with good weather resistance up to one year.

Туре

Film

 Tensile MD
 Tensile CD

 15200 Psi
 26800 Psi

 Elong MD
 Elong CD

 70
 55

PROPERTIES VALUE

Caliper 2.60 Mil

Opacity 90

REGULATORY APPROVAL

 RoHS
 Prop65
 REACH

 Yes
 Yes
 Yes

 TPCH
 CPSIA
 FSC

 Yes
 Yes
 No

ADHESIVE

Glass

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

TypeCompositionShearPermanentAcrylic350

Min. Application Temperature Min. Service Temperature Max. Application Temperature

35 F -65 F 200 F

2,8lbs/linear in.

PROPERTIES VALUE

Stainless Steel 5.6 lbs/linear in.

Polyethylene 2.9

Corrugated 1.50 lbs./in.

Painted Metal 4.9 lbs/linear in.

Loop Tack 2.70 oz/in²

^{*}Please contact your sales representative for details

REGULATORY APPROVAL

RoHS Prop65 **REACH** No Yes Yes

CPSIA TPCH Direct Food

Yes No Yes

Indirect Food

Yes

*Please contact your sales representative for details

LINER

A 1.5 mil polyester liner which has been silicone coated one side to give a controlled release. It has extremely high internal strength for ease in manufacturing, converting and end usage, making it an outstanding liner for high speed, automatic applications.

Туре 619827

Tensile MD Tensile CD

32000

Tear MD **Tear CD** 0 0

DESCRIPTION VALUE

Caliper 1.5

REGULATORY APPROVAL

RoHS Prop65 **REACH** Yes Yes Yes **CPSIA TPCH** UL Yes Yes No

Direct Food

No

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Туре 5517353

40

Tensile CD Tensile MD 24

Tear MD Tear CD 44 48

DESCRIPTION VALUE

Basis Weight 50

^{*}Please contact your sales representative for details

Caliper	3.2		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	UL	
Yes	Yes	No	
Direct Food			
No			
*Dl	- ununun authotiva fau dataila		
*Please contact your sales representative for details			

Last update: 02/11/2025

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448

orders.us@beontag.com