

2 MIL BRIGHT SILVER TC POLYESTER / TS523 @ 1.5 Cwt. / 50#SCK L-3

ITEM #4801

<b>FACESTOCK</b> This versatile top-coating is compatible with solvent base, water base, and UV curable inks, as well as silk screen, flexographic and offset/letterpress printing.		
<b>Type</b> Film		
<b>Tensile MD</b> 28000 Psi	<b>Tensile CD</b> 34000 Psi	
<b>Tear MD</b> 1500 Grams		
<b>Elong MD</b> 300	<b>Elong CD</b> 110	
<b>PROPERTIES</b>	<b>VALUE</b>	
<b>Caliper</b>	2.00 Mil	
<b>REGULATORY APPROVAL</b>		
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>FSC</b> No
*Please contact your sales representative for details		

<b>ADHESIVE</b> A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.		
<b>Type</b> Permanent	<b>Composition</b> Acrylic	<b>Shear</b> 350
<b>Min. Application Temperature</b> 35 F	<b>Min. Service Temperature</b> -65 F	<b>Max. Application Temperature</b> 200 F
<b>PROPERTIES</b>	<b>VALUE</b>	
<b>Stainless Steel</b>	5.6 lbs/linear in.	
<b>Glass</b>	2,8lbs/linear in.	
<b>Polyethylene</b>	2.9	
<b>Corrugated</b>	1.50 lbs./in.	
<b>Painted Metal</b>	4.9 lbs/linear in.	

Loop Tack

2.70 oz/in<sup>2</sup>

REGULATORY APPROVAL

RoHS  
Yes

Prop65  
No

REACH  
Yes

TPCH  
Yes

CPSIA  
Yes

Direct Food  
No

Indirect Food  
Yes

\*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type  
5517353

Tensile MD  
40

Tensile CD  
24

Tear MD  
44

Tear CD  
48

DESCRIPTION

VALUE

Basis Weight

50

Caliper

3.2

REGULATORY APPROVAL

RoHS  
Yes

Prop65  
Yes

REACH  
Yes

TPCH  
Yes

CPSIA  
Yes

UL  
No

Direct Food  
No

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:  
Beontag  
6206 Wolf Creek Pike  
Trotwood, OH 45426  
[800-358-4448](tel:800-358-4448)  
[orders.us@beontag.com](mailto:orders.us@beontag.com)