



Pressure-sensitive adhesives

Acrylic

Film

2 MIL CRYSTAL CLEAR BOPP / TS523 @ 1.5 Cwt. / 40#SCK L-3

ITEM #75772

FACESTOCK A 2 mil clear biaxially oriented polypropylene with exceptional clarity, excellent die-cut performance and great stiffness. Coated gloss surface is print receptive for standard methods.		
Type Film		
Tensile MD 20,000 psi	Tensile CD 35,000 psi	
Elong MD 180	Elong CD 55%	
PROPERTIES		
Caliper	2.00 Mil	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
FSC No		
*Please contact your sales representative for details		

ADHESIVE A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.		
Type Permanent	Composition Acrylic	Shear 350
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 200 F
PROPERTIES	VALUE	
Stainless Steel	5.6 lbs/linear in.	
Glass	2,8lbs/linear in.	
Polyethylene	2.9	
Corrugated	1.50 lbs./in.	
Painted Metal	4.9 lbs/linear in.	

Loop Tack			2.70 oz/in ²
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	No	Yes	
TPCH	CPSIA	Direct Food	
Yes	Yes	No	
Indirect Food			
Yes			
*Please contact your sales representative for details			

LINER		
Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type 5517342		
Tensile MD 34	Tensile CD 22	
Tear MD 32	Tear CD 34	
DESCRIPTION		
Basis Weight	40	
Caliper	2.5	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com