

2 MIL CRYSTAL CLEAR POLYPROP TF335 / LPG 40#SCK

ITEM #75676

FACESTOCK A 2 mil clear biaxially oriented polypropylene with exceptional clarity, excellent die-cut performance and great stiffness. Coated gloss surface is print receptive for standard methods.		
Type Film		
Tensile MD 20,000 psi	Tensile CD 35,000 psi	
Elong MD 180	Elong CD 55%	
PROPERTIES		
Caliper	2.00 Mil	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
FSC No		
*Please contact your sales representative for details		

ADHESIVE A freezer grade rubber based adhesive with good initial tack and good ultimate adhesion when applied at temperatures as low as -20 F. This is a firm, minimal cold flow adhesive. A true freezer grade adhesive that is very permanent at cold temps, yet semi-removable at room temps.		
Type Permanent	Composition Latex	Shear 50
Min. Application Temperature -20 F	Min. Service Temperature -65 F	Max. Application Temperature 140 F
PROPERTIES	VALUE	
Stainless Steel	2.6 lbs/linear in.	
Glass	0lbs/linear in.	
Polyethylene	2,2	
Loop Tack	2.00 oz/in ²	

REGULATORY APPROVAL

RoHS
Yes

Prop65
No

REACH
Yes

TPCH
Yes

CPSIA
Yes

Direct Food
Yes

Indirect Food
Yes

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type
5517342

Tensile MD
34

Tensile CD
22

Tear MD
32

Tear CD
34

DESCRIPTION

VALUE

Basis Weight

40

Caliper

2.5

REGULATORY APPROVAL

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

UL
No

Direct Food
No

*Please contact your sales representative for details

Last update: 10/21/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com