

2 MIL MATTE SILVER CP POLYESTER / TS523 @ 1.5 Cwt. / 8PT TAG L-3

ITEM #84254

FACESTOCK A 2 mil silver top-coated polyester with a very smooth matte finish. It has excellent tear strength, heat resistance and dimensional stability, while the CP top-coating allows for laser, thermal transfer and most standard ink receptivity.		
Type Film		
Tensile MD 28000 Psi	Tensile CD 34000 Psi	
Tear MD 1400 Grams		
Elong MD 300	Elong CD 110	
PROPERTIES	VALUE	
Caliper	2.00 Mil	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No
*Please contact your sales representative for details		

ADHESIVE A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.		
Type Permanent	Composition Acrylic	Shear 350
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 200 F
PROPERTIES	VALUE	
Stainless Steel	5.6 lbs/linear in.	
Glass	2,8lbs/linear in.	
Polyethylene	2.9	
Corrugated	1.50 lbs./in.	
Painted Metal	4.9 lbs/linear in.	

Loop Tack

2.70 oz/in²

REGULATORY APPROVAL

RoHS
Yes

Prop65
No

REACH
Yes

TPCH
Yes

CPSIA
Yes

Direct Food
No

Indirect Food
Yes

*Please contact your sales representative for details

LINER

An 8pt, 100# tag liner which has been silicone coated one side to give a controlled release. It has exceptionally high internal strength to withstand all conventional processing operations including die-cutting, perforating, fanfolding and refolding processes.

Type
17380

Tensile MD
63

Tensile CD
34

Tear MD
149

Tear CD
156

DESCRIPTION

VALUE

Basis Weight

102

Caliper

8

REGULATORY APPROVAL

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

UL
No

Direct Food
No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com