



Pressure-sensitive adhesives

Acrylic

Film

2 MIL METALLIZED CLEAR TOPCOATED BOPP / TS585WS @ 1.6 Cwt. / 44#PK L-3

ITEM #8810047

FACESTOCK A 2 mil coated one side metallized BOPP designed for high sheen, metallized appearance and high-speed press performance. Typical applications are beverage, health and beauty and pharmaceutical. Outstanding water based flexo, UV flexo, UV letterpress and rotary screen ink adhesion.		
Type Film		
Tensile MD 137.5 PSI	Tensile CD 241 PSI	
Elong MD 180	Elong CD 55	
PROPERTIES		
Caliper	2.0	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No
*Please contact your sales representative for details		

ADHESIVE A specialty adhesive designed to adhere to slightly wet surfaces with good ultimate adhesion when applied at temperatures as low as -20 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for hard to label substrates.		
Type Permanent	Composition Acrylic	Shear 65
Min. Application Temperature -20 F	Min. Service Temperature -65 F	Max. Application Temperature 140 F
PROPERTIES	VALUE	
Stainless Steel	4.8 lbs/linear in.	
Glass	3,2lbs/linear in.	
Polyethylene	6,5lbs/linear in.	
Corrugated	1.45 lbs./in.	
Painted Metal	4.4 lbs/linear in.	

Loop Tack		2.70 oz/in ²	
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	No	Yes	
TPCH	CPSIA	Direct Food	
Yes	Yes	No	
Indirect Food			
Yes			
*Please contact your sales representative for details			

LINER		
A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.		
Type 17745		
Tensile MD 35	Tensile CD 13	
Tear MD 35	Tear CD 50	
DESCRIPTION		
Basis Weight	44	
Caliper	3.2	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com