

2 MIL TC METALLIZED BOPP / TR440 @ 1.0 Cwt. / 40#SCK L-3

ITEM #1458

FACESTOCK A 2 mil coated one side metallized BOPP designed for high sheen, metallized appearance and high-speed press performance. Typical applications are beverage, health and beauty and pharmaceutical. Outstanding water based flexo, UV flexo, UV letterpress and rotary screen ink adhesion.		
Type Film		
Tensile MD 137.5 PSI	Tensile CD 241 PSI	
Elong MD 180	Elong CD 55	
PROPERTIES	VALUE	
Caliper	2.0	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No
*Please contact your sales representative for details		

ADHESIVE A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces.		
Type Removable	Composition Acrylic	Shear 110
Min. Application Temperature 40 F	Min. Service Temperature -65 F	Max. Application Temperature 150 F
PROPERTIES	VALUE	
Stainless Steel	4.7 lbs/linear in.	
Glass	3lbs/linear in.	
Polyethylene	1.4	
Corrugated	1.20 lbs./in.	
Painted Metal	4.2 lbs/linear in.	
Loop Tack	1.70 oz/in ²	

REGULATORY APPROVAL

RoHS
Yes

Prop65
No

REACH
Yes

TPCH
Yes

CPSIA
Yes

Direct Food
No

Indirect Food
Yes

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type
5517342

Tensile MD
34

Tensile CD
22

Tear MD
32

Tear CD
34

DESCRIPTION

VALUE

Basis Weight

40

Caliper

2.5

REGULATORY APPROVAL

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

UL
No

Direct Food
No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com