

2.3 MIL MAJESTIC WHITE BOPP / AP151 @ 1.3 Cwt. / 40#SCK L-3

ITEM #151370

FACESTOCK A topcoated white polypropylene film with a gloss level of 48%. Product has excellent printability (Thermal Transfer printability with a resin ribbon only), temperature resistance & semi squeezable performance. This face offers balanced orientation for superior die cutting and high stiffness for conversion and automatic dispensing.		
Type Film		
Tensile MD 25400 Psi	Tensile CD 22500 Psi	
Elong MD 95	Elong CD 115	
PROPERTIES		
Caliper	2.30 Mil	
Opacity	80	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No
*Please contact your sales representative for details		

ADHESIVE An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.		
Type Permanent	Composition Latex	Shear 80
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 220 F
PROPERTIES	VALUE	
Stainless Steel	7.3 lbs/linear in.	
Glass	5.7 lbs/linear in.	
Polyethylene	6.5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	

Loop Tack		5.00 oz/in ²
REGULATORY APPROVAL		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		
*Please contact your sales representative for details		

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34

Tear MD

32

Tensile CD

22

Tear CD

34

DESCRIPTION

VALUE

Basis Weight

40

Caliper

2.5

REGULATORY APPROVAL

RoHS

Yes

TPCH

Yes

Direct Food

No

Prop65

Yes

CPSIA

Yes

REACH

Yes

UL

No

*Please contact your sales representative for details

Last update: 08/20/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com