

2.3 MIL MAJESTIC WHITE BOPP / TS523 @ 1.5 Cwt. / 50#SCK L-3

ITEM #2395

| | | |
|---|--------------------------------|---------------------|
| FACESTOCK A topcoated white polypropylene film with a gloss level of 48%. Product has excellent printability (Thermal Transfer printability with a resin ribbon only), temperature resistance & semi squeezable performance. This face offers balanced orientation for superior die cutting and high stiffness for conversion and automatic dispensing. | | |
| Type Film | | |
| Tensile MD 25400 Psi | Tensile CD 22500 Psi | |
| Elong MD 95 | Elong CD 115 | |
| PROPERTIES | | |
| Caliper | 2.30 Mil | |
| Opacity | 80 | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | FSC No |
| *Please contact your sales representative for details | | |

| | | |
|---|--|--|
| ADHESIVE A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive. | | |
| Type Permanent | Composition Acrylic | Shear 350 |
| Min. Application Temperature 35 F | Min. Service Temperature -65 F | Max. Application Temperature 200 F |
| PROPERTIES | VALUE | |
| Stainless Steel | 5.6 lbs/linear in. | |
| Glass | 2,8lbs/linear in. | |
| Polyethylene | 2.9 | |
| Corrugated | 1.50 lbs./in. | |
| Painted Metal | 4.9 lbs/linear in. | |
| Loop Tack | 2.70 oz/in ² | |

REGULATORY APPROVAL**RoHS**

Yes

Prop65

No

REACH

Yes

TPCH

Yes

CPSIA

Yes

Direct Food

No

Indirect Food

Yes

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517353

Tensile MD

40

Tensile CD

24

Tear MD

44

Tear CD

48

DESCRIPTION**VALUE****Basis Weight**

50

Caliper

3.2

REGULATORY APPROVAL**RoHS**

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

*Please contact your sales representative for details

Last update: 08/20/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426

800-358-4448

orders.us@beontag.com