

2.3 mil Pearl White BOPP / TR440 @ 1.0 Cwt. / 40#SCK L-3

ITEM #95291

| | | |
|--|-------------------------|---------------------|
| FACESTOCK A coated one side BOPP face stock with excellent stability and cutting capabilities. This film has excellent stiffness, gloss, and opacity. Excellent whiteness and opacity. | | |
| Type Film | | |
| Tensile MD 7 | Tensile CD 15 | |
| Elong MD 160 | Elong CD 30 | |
| PROPERTIES | VALUE | |
| Caliper | 2.3 | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | FSC No |
| *Please contact your sales representative for details | | |

| | | |
|---|--|--|
| ADHESIVE A specialty clear acrylic adhesive showing good initial removable tack with high shear and high removable adhesion. This adhesive has excellent clarity & minimum cold flow. Good removability on a wide range of substrates including corrugated and many plastic surfaces. | | |
| Type Removable | Composition Acrylic | Shear 110 |
| Min. Application Temperature 40 F | Min. Service Temperature -65 F | Max. Application Temperature 150 F |
| PROPERTIES | VALUE | |
| Stainless Steel | 4.7 lbs/linear in. | |
| Glass | 3lbs/linear in. | |
| Polyethylene | 1.4 | |
| Corrugated | 1.20 lbs./in. | |
| Painted Metal | 4.2 lbs/linear in. | |
| Loop Tack | 1.70 oz/in ² | |

REGULATORY APPROVAL

RoHS
Yes

Prop65
No

REACH
Yes

TPCH
Yes

CPSIA
Yes

Direct Food
No

Indirect Food
Yes

*Please contact your sales representative for details

LINER

A super calendared kraft paper which has been silicone coated one side to give a controlled release. This paper has a hard, smooth caliper for a consistent surface. Due to it's high internal strength, it will withstand all conventional processing operations including: die-cutting, butt cutting, line scoring, and dispersing.

Type
5517342

Tensile MD
30 Lbs/In

Tensile CD
20 Lbs/In

Tear MD
32 Grams

Tear CD
34 Grams

DESCRIPTION

VALUE

Basis Weight

40.5 Lbs/Rm

Caliper

2.5 Mil

REGULATORY APPROVAL

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

UL
No

Direct Food
No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com