

Pressure-sensitive adhesives

Acrylic

Film

# 2.3 MIL POLAR WHITE BOPP / AT333 @ 1.30 Cwt. / 1.2 MIL PET L-3

## ITEM #7772157

## **FACESTOCK**

A 2.3 mil white BOPP with a 50% gloss level. Outstanding whiteness and opacity. Topcoated for printability using standard print methods and thermal transfer (with resin ribbon only). This film has high machine direction stiffness and tensile strength for superior high speed label dispensing.

Туре

Film

 Tensile MD
 Tensile CD

 20000 Psi
 35000 Psi

 Elong MD
 Elong CD

 180
 60

PROPERTIES VALUE

Caliper 2.30 Mil

Opacity 89

# REGULATORY APPROVAL

RoHS<br/>YesProp65<br/>YesREACH<br/>YesTPCH<br/>YesCPSIA<br/>YesUL<br/>No

FSC No

## **ADHESIVE**

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Туре	Composition	Shear
Permanent	Acrylic	60

Min. Application Temperature Min. Service Temperature Max. Application Temperature

0 F \_-65 F

-20 F	-65 F	160 F	
PROPERTIES	VALUE		
Stainless Steel	4.7 lbs/linear in.		
Glass	1,3lbs/linear in.		
Polyethylene	2.2		
Corrugated	1.40 lbs./in.		

<sup>\*</sup>Please contact your sales representative for details

**Painted Metal** 4.4 lbs/linear in.

2.20 oz/in<sup>2</sup> **Loop Tack** 

**REGULATORY APPROVAL** 

Prop65 **REACH RoHS** Yes No Yes

**TPCH CPSIA Direct Food** 

Yes Yes No

**Indirect Food** 

Yes

\*Please contact your sales representative for details

## **LINER**

An economical 1.2 mil clear polyester film liner good for an array of prime label applications.

**Tensile MD Tensile CD** 

30000 0

**Tear MD Tear CD** 0 0

**DESCRIPTION VALUE** 

0 **Basis Weight** 

Caliper 1.2

## **REGULATORY APPROVAL**

**RoHS** Prop65 **REACH** Yes Yes Yes

**TPCH CPSIA** Yes Yes

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448 orders.us@beontag.com