#### Pressure-sensitive adhesives

Acrylic Film

# 2.6 MIL LABEL LYTE / TS523 @ 1.5 Cwt. / 50#SCK L-3

ITEM #5015

## FACESTOCK

A 2.6 mil heat set, biaxially oriented multi-layer white polypropylene film. It is designed for excellent opacity and has a high surface treatment for good ink adhesion while maintaining it\'s pearlescent look.

Туре		
Film		
Tensile MD	Tensile CD	
13000 Psi	25000 Psi	
13000 PSI	2000 PSI	
Elong MD	Elong CD	
100	50	
PROPERTIES	VALUE	
FNOFEITIES		
Caliper	2.60 Mil	
Opacity	88	
opacity	00	
REGULATORY APPROVAL		
Prop65	FSC	
Yes	No	
*Please contact your sales represe	ntative for details	

## **ADHESIVE**

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

<b>Type</b> Permanent	<b>Composition</b> Acrylic	<b>Shear</b> 350
<b>Min. Application Temperature</b> 35 F	<b>Min. Service Temperature</b> -65 F	<b>Max. Application Temperature</b> 200 F
PROPERTIES	VALUE	
Stainless Steel	5.6 lbs/linear in.	
Glass	2,8lbs/linear in.	
Polyethylene	2.9	
Corrugated	1.50 lbs./in.	
Painted Metal	4.9 lbs/linear in.	
Loop Tack	2.70 oz/in <sup>2</sup>	

REGULATORY APPROVAL				
<b>RoHS</b>	Prop65	<b>REACH</b>		
Yes	No	Yes		
<b>TPCH</b>	<b>CPSIA</b>	<b>Direct Food</b>		
Yes	Yes	No		
Indirect Food				

Yes

\*Please contact your sales representative for details

## LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

<b>Туре</b> 5517353				
Tensile MD	Tensile CD			
40	24			
Tear MD	Tear CD			
44	48			
DESCRIPTION	VALUE			
Basis Weight	50			
Caliper	3.2			
REGULATORY APPROVAL				
RoHS	Prop65	REACH		
Yes	Yes	Yes		
ТРСН	CPSIA	UL		
Yes	Yes	No		
<b>Direct Food</b> No				
*Please contact your sales representative for details				

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS: Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448 orders.us@beontag.com