c <u>Film</u>

# 2.6 MIL MATTE WH BOPP P / B TS523 1.5 MIL TS523 40#SCK L-3

ITEM #86602

## FACESTOCK

A 2.6 Mil matte white polypropylene film that is designed for thermal transfer printability. Features good weather resistance and dimensional stability.

<b>Туре</b> Film			
Tensile MD	Tensile CD		
13800	26800		
Elong MD	Elong CD		
170	55		
PROPERTIES	VALUE		
Caliper	2.6 mil		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
fes	Yes	Yes	
ГРСН	CPSIA	FSC	
Yes	Yes	No	

\*Please contact your sales representative for details

### ADHESIVE

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

<b>Type</b> Permanent	<b>Composition</b> Acrylic	Shear 350
<b>Min. Application Temperature</b> 35 F	<b>Min. Service Temperature</b> -65 F	<b>Max. Application Temperature</b> 200 F
PROPERTIES	VALUE	
Stainless Steel	5.6 lbs/linear in.	
Glass	2,8lbs/linear in.	
Polyethylene	2.9	
Corrugated	1.50 lbs./in.	
Painted Metal	4.9 lbs/linear in.	
Loop Tack	2.70 oz/in <sup>2</sup>	

REGULATORY APPROVAL			
<b>RoHS</b>	Prop65	<b>REACH</b>	
Yes	No	Yes	
<b>трсн</b>	<b>CPSIA</b>	<b>Direct Food</b>	
Yes	Yes	No	

\*Please contact your sales representative for details

#### LINER

A 1.5 mil polyester liner which has been silicone coated one side to give a controlled release. It has extremely high internal strength for ease in manufacturing, converting and end usage, making it an outstanding liner for high speed, automatic applications.

<b>Туре</b> 619827			
<b>Tensile MD</b> 32000	<b>Tensile CD</b> ()		
<b>Tear MD</b> 0	<b>Tear CD</b> ()		
DESCRIPTION	VALUE		
Caliper	1.5		
REGULATORY APPROVAL			
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes	
<b>трсн</b> Yes	<b>CPSIA</b> Yes	ul No	
<b>Direct Food</b> No			
*Please contact your sales rep	resentative for details		

#### LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

<b>Туре</b> 5517342	
<b>Tensile MD</b> 34	Tensile CD 22
<b>Tear MD</b> 32	Tear CD 34
DESCRIPTION	VALUE
Basis Weight	40

Caliper	2.5		
REGULATORY APPROVAL			
<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes	
<b>трсн</b> Yes	<b>CPSIA</b> Yes	UL No	
<b>Direct Food</b> No			
*Please contact your sales repr	esentative for details		

~ -

Last update: 05/01/2024

...

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG's standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS: Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 <u>800-358-4448</u> <u>orders.us@beontag.com</u>