

Pressure-sensitive adhesives

Acrylic

Film

2.6 MIL MATTE WHITE TT BOPP P / B TP170 40#SCK TP170 50#SCK

ITEM #286683

FACESTOCK

A 2.6 Mil matte white C2S, antistatic polypropylene film that is designed for thermal transfer printability. Features excellent print resolution and abrasion resistance with good weather resistance up to one year.

Туре

Film

 Tensile MD
 Tensile CD

 15200 Psi
 26800 Psi

 Elong MD
 Elong CD

 70
 55

PROPERTIES VALUE

Caliper 2.60 Mil

Opacity 90

REGULATORY APPROVAL

 RoHS
 Prop65
 REACH

 Yes
 Yes
 Yes

 TPCH
 CPSIA
 FSC

 Yes
 Yes
 No

ADHESIVE

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

TypeCompositionShearPermanentAcrylic300

Min. Application Temperature Min. Service Temperature Max. Application Temperature

35 F -65 F 180 F

PROPERTIES VALUE

Stainless Steel 5.2 lbs/linear in.

Glass 3,2lbs/linear in.

Polyethylene 1.6

Corrugated 1.40 lbs./in.

Painted Metal 5.2 lbs/linear in.

Loop Tack 2.20 oz/in²

^{*}Please contact your sales representative for details

REGULATORY APPROVAL

RoHSProp65REACHYesNoYes

TPCH CPSIA Direct Food

Yes Yes No

Indirect Food

Yes

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Туре

5517342

Tensile MD Tensile CD

34 22

 Tear MD
 Tear CD

 32
 34

DESCRIPTION	VALUE
Basis Weight	40
Caliper	2.5

REGULATORY APPROVAL

 RoHS
 Prop65
 REACH

 Yes
 Yes
 Yes

 TPCH
 CPSIA
 UL

 Yes
 No
 No

Direct Food

No

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type 5517353

Tensile MD Tensile CD

40 24

 Tear MD
 Tear CD

 44
 48

DESCRIPTION VALUE

^{*}Please contact your sales representative for details

Basis Weight Caliper	50 3.2		
•			
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	UL	
Yes	Yes	No	
Direct Food No			
*Please contact your sales representative for details			

Last update: 08/19/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448 orders.us@beontag.com