



Pressure-sensitive adhesives

Acrylic

Acrylic

Film

2.6 MIL PEARL WHITE BOPP / AT333 @ 1.7 Cwt / 40#SCK / AT333 / 40#SCK

ITEM #86688

FACESTOCK A top coated white cavitated BOPP face stock with excellent stability and die cutting capabilities. Printability includes water, solvent, and UV based inks on flexo, gravure, UV letterpress and rotary screen printing systems. It is also thermal transfer printable. This film has excellent stiffness, gloss, and opacity.	
Type Film	
Tensile MD 11360 Psi	Tensile CD 22580 Psi
Elong MD 140	Elong CD 47
PROPERTIES	VALUE
Caliper	2.60 Mil
REGULATORY APPROVAL	
Prop65 Yes	FSC No
*Please contact your sales representative for details	

ADHESIVE An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.		
Type Permanent	Composition Acrylic	Shear 60
Min. Application Temperature -20 F	Min. Service Temperature -65 F	Max. Application Temperature 160 F
PROPERTIES	VALUE	
Stainless Steel	5.3 lbs/linear in.	
Glass	1,3lbs/linear in.	
Polyethylene	2.2	
Corrugated	1.50 lbs./in.	
Painted Metal	5.1 lbs/linear in.	
Loop Tack	2.40 oz/in²	

REGULATORY APPROVAL**RoHS**

Yes

Prop65

No

REACH

Yes

TPCH

Yes

CPSIA

Yes

Direct Food

No

Indirect Food

Yes

*Please contact your sales representative for details

ADHESIVE

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Type

Permanent

Composition

Acrylic

Shear

60

Min. Application Temperature

-20 F

Min. Service Temperature

-65 F

Max. Application Temperature

160 F

PROPERTIES**VALUE****Stainless Steel**

4.7 lbs/linear in.

Glass

1,3lbs/linear in.

Polyethylene

2.2

Corrugated

1.40 lbs./in.

Painted Metal

4.4 lbs/linear in.

Loop Tack2.20 oz/in²**REGULATORY APPROVAL****RoHS**

Yes

Prop65

No

REACH

Yes

TPCH

Yes

CPSIA

Yes

Direct Food

No

Indirect Food

Yes

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34

Tensile CD

22

Tear MD

32

Tear CD

34

DESCRIPTION			VALUE
Basis Weight			40
Caliper			2.5
REGULATORY APPROVAL			
RoHS		Prop65	REACH
Yes		Yes	Yes
TPCH		CPSIA	UL
Yes		Yes	No
Direct Food			
No			
*Please contact your sales representative for details			

Last update: 08/20/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com