

## 2.6 MIL TC PEARL WHITE BOPP AP151 HCWT 1.2 MIL PET

ITEM #95234

|  |                         |                     |
|--|-------------------------|---------------------|
| <b>FACESTOCK</b><br>A coated one side BOPP face stock with excellent stability and cutting capabilities. This film has excellent stiffness, gloss, and opacity. Excellent whiteness and opacity. |                         |                     |
| <b>Type</b><br>Film  |                         |                     |
| <b>Tensile MD</b><br>7   | <b>Tensile CD</b><br>15 |                     |
| <b>Elong MD</b><br>160   | <b>Elong CD</b><br>30   |                     |
| <b>PROPERTIES</b>  | <b>VALUE</b>            |                     |
| <b>Caliper</b>   | 2.3                     |                     |
| <b>REGULATORY APPROVAL</b>   |                         |                     |
| <b>RoHS</b><br>Yes   | <b>Prop65</b><br>Yes    | <b>REACH</b><br>Yes |
| <b>TPCH</b><br>Yes   | <b>CPSIA</b><br>Yes     | <b>FSC</b><br>No    |
| *Please contact your sales representative for details  |                         |                     |

|  |                             |
|--|-----------------------------|
| <b>ADHESIVE</b><br>An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits. |                             |
| <b>Type</b><br>Permanent   | <b>Composition</b><br>Latex |
| <b>PROPERTIES</b>  | <b>VALUE</b>                |
| <b>Stainless Steel</b>   | 7.5 lbs/linear in.          |
| <b>Glass</b>   | 5.7 lbs/linear in.          |
| <b>Polyethylene</b>  | 6,5                         |
| <b>Corrugated</b>  | 2.70 lbs./in.               |
| <b>Painted Metal</b>   | 7.5 lbs/linear in.          |
| <b>Loop Tack</b>   | 5.20 oz/in <sup>2</sup>     |
| <b>REGULATORY APPROVAL</b>   |                             |

**RoHS**  
Yes

**Prop65**  
No

**REACH**  
Yes

**TPCH**  
Yes

**CPSIA**  
Yes

**Direct Food**  
No

**Indirect Food**  
Yes

\*Please contact your sales representative for details

Last update: 10/21/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag  
6206 Wolf Creek Pike  
Trotwood, OH 45426  
[800-358-4448](tel:800-358-4448)  
[orders.us@beontag.com](mailto:orders.us@beontag.com)