

## 3.6 MIL POLYART / AP151 @ 1.3 Cwt. GRAY OPAQUE / 50#SCK L-3

ITEM #6800

<b>FACESTOCK</b>		
<p>A high performance polyethylene base synthetic paper with a unique computer printable top coating allowing Polyart to be printed with flexo, litho, gravure, letterpress and screen methods. It can also be used with thermal transfer, ion dep and dot matrix.</p>		
<b>Type</b>		
Film		
<b>Tensile MD</b>	<b>Tensile CD</b>	
6670 Psi	5510 Psi	
<b>Tear MD</b>	<b>Tear CD</b>	
496 Grams	599 Grams	
<b>Elong MD</b>	<b>Elong CD</b>	
120	110	
PROPERTIES	VALUE	
<b>Caliper</b>	3.60 Mil	
<b>Opacity</b>	90	
<b>REGULATORY APPROVAL</b>		
<b>RoHS</b>	<b>Prop65</b>	<b>REACH</b>
Yes	Yes	Yes
<b>TPCH</b>	<b>CPSIA</b>	<b>FSC</b>
Yes	Yes	No
*Please contact your sales representative for details		

<b>ADHESIVE</b>		
<p>An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting &amp; stripping traits.</p>		
<b>Type</b>	<b>Composition</b>	<b>Shear</b>
Permanent	Latex	80
<b>Min. Application Temperature</b>	<b>Min. Service Temperature</b>	<b>Max. Application Temperature</b>
35 F	-65 F	220 F
PROPERTIES	VALUE	
<b>Stainless Steel</b>	7.3 lbs/linear in.	
<b>Glass</b>	5.7 lbs/linear in.	
<b>Polyethylene</b>	6.5	
<b>Corrugated</b>	2.50 lbs./in.	
<b>Painted Metal</b>		

7.0 lbs/linear in.

**Loop Tack**

5.00 oz/in<sup>2</sup>

**REGULATORY APPROVAL**

**RoHS**  
Yes

**Prop65**  
No

**REACH**  
Yes

**TPCH**  
Yes

**CPSIA**  
Yes

**Direct Food**  
No

**Indirect Food**  
Yes

\*Please contact your sales representative for details

**LINER**

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

**Type**

5517353

**Tensile MD**

40

**Tensile CD**

24

**Tear MD**

44

**Tear CD**

48

**DESCRIPTION**

**VALUE**

**Basis Weight**

50

**Caliper**

3.2

**REGULATORY APPROVAL**

**RoHS**  
Yes

**Prop65**  
Yes

**REACH**  
Yes

**TPCH**  
Yes

**CPSIA**  
Yes

**UL**  
No

**Direct Food**  
No

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag  
6206 Wolf Creek Pike  
Trotwood, OH 45426

800-358-4448

[orders.us@beontag.com](mailto:orders.us@beontag.com)