

3.6 MIL POLYART / TR447 @ 1.4 Cwt. / 50#SCK L-3

ITEM #89351

FACESTOCK

A high performance polyethylene base synthetic paper with a unique computer printable top coating allowing Polyart to be printed with flexo, litho, gravure, letterpress and screen methods. It can also be used with thermal transfer, ion dep and dot matrix.

Type
Film

Tensile MD
6670 Psi

Tensile CD
5510 Psi

Tear MD
496 Grams

Tear CD
599 Grams

Elong MD
120

Elong CD
110

PROPERTIES

VALUE

Caliper

3.60 Mil

Opacity

90

REGULATORY APPROVAL

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

FSC
No

*Please contact your sales representative for details

ADHESIVE

A general purpose, removable rubber based emulsion adhesive featuring good initial tack and moderate adhesion. It has limited plasticizer, UV and solvent resistance. This is a standard removable adhesive for tape reels, computer disks and kids stickers.

Type
Removable

Composition
Latex

Shear
40

Min. Application Temperature
40 F

Min. Service Temperature
1 F

Max. Application Temperature
120 F

PROPERTIES

VALUE

Stainless Steel

2.5 lbs/linear in.

Glass

0,9lbs/linear in.

Polyethylene

1,8

Corrugated

1.00 lbs./in.

Painted Metal 1.6 lbs/linear in.
Loop Tack 1.50 oz/in²

REGULATORY APPROVAL

RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type
5517353

Tensile MD 40	Tensile CD 24
-------------------------	-------------------------

Tear MD 44	Tear CD 48
----------------------	----------------------

DESCRIPTION	VALUE
-------------	-------

Basis Weight	50
---------------------	----

Caliper	3.2
----------------	-----

REGULATORY APPROVAL

RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com