

3.6 MIL POLYART TS523 65# C2S

ITEM #78061

FACESTOCK A high performance polyethylene base synthetic paper with a unique computer printable top coating allowing Polyart to be printed with flexo, litho, gravure, letterpress and screen methods. It can also be used with thermal transfer, ion dep and dot matrix.		
Type Film		
Tensile MD 6670 Psi	Tensile CD 5510 Psi	
Tear MD 496 Grams	Tear CD 599 Grams	
Elong MD 120	Elong CD 110	
PROPERTIES		VALUE
Caliper		3.60 Mil
Opacity		90
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No
*Please contact your sales representative for details		

ADHESIVE A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.		
Type Permanent	Composition Acrylic	Shear 350
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 200 F
PROPERTIES	VALUE	
Stainless Steel	5.6 lbs/linear in.	
Glass	2,8lbs/linear in.	
Polyethylene	2.9	
Corrugated	1.50 lbs./in.	

Painted Metal	4.9 lbs/linear in.	
Loop Tack	2.70 oz/in ²	
REGULATORY APPROVAL		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		
*Please contact your sales representative for details		

LINER		
Fully Bleached Kraft (FBK) liner which has been silicone coated one side to give a controlled release. It is designed to withstand all die-cutting, marginal punching, perforating, fanfolding and refolding processes. It is an excellent lay-flat liner.		
Type 47365		
Tensile MD 33 Lbs/In	Tensile CD 18 Lbs/In	
Tear MD 60 Grams	Tear CD 60 Grams	
DESCRIPTION		
VALUE		
Basis Weight	63 Lbs/Rm	
Caliper	3.8	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

LINER		
Fully Bleached Kraft (FBK) liner which has been silicone coated one side to give a controlled release. It is designed to withstand all die-cutting, marginal punching, perforating, fanfolding and refolding processes. It is an excellent lay-flat liner.		
Type 47365		
Tensile MD 33 Lbs/In	Tensile CD 18 Lbs/In	
Tear MD 60 Grams	Tear CD 60 Grams	

DESCRIPTION	VALUE	
Basis Weight	63 Lbs/Rm	
Caliper	3.8 Mil	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com