

Pressure-sensitive adhesives

Acrylic

3.7 MIL SMUDGE KIMDURA / AT333 @ 1.30 Cwt. / 40#SCK L-3

ITEM #8996

FACESTOCK

A 3.7 mil white Smudge Kimdura which is a biaxially oriented three ply polypropylene which combines extraordinary edge tear resistance with a smooth, uniform surface that provides brilliant imagery, superior print quality and smudge resistance.

Туре Film

Tensile MD

Tensile CD 24 Lbs/in 18 Lbs/in **Tear MD Tear CD** 26 Grams 15 Grams

PROPERTIES

VALUE

Caliper

3.70 Mil

REGULATORY APPROVAL

RoHS Prop65 **REACH** Yes Yes Yes **TPCH CPSIA FSC** Yes Yes No

ADHESIVE

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Туре	Composition	Shear
Permanent	Acrylic	60

Min. Application Temperature Max. Application Temperature Min. Service Temperature

-20 F	-65 F	160 F
PROPERTIES	VALUE	
Stainless Steel	4.7 lbs/linear in.	
Glass	1,3lbs/linear in.	
Polyethylene	2.2	
Corrugated	1.40 lbs./in.	
Painted Metal	4.4 lbs/linear in.	
Loop Tack	2.20 oz/in ²	

^{*}Please contact your sales representative for details

REGULATORY APPROVAL

RoHS Prop65 **REACH** Yes No Yes

TPCH CPSIA Direct Food

Yes Yes No

Indirect Food

Yes

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Туре

5517342

Tensile MD Tensile CD

34 22

Tear MD Tear CD 34 32

DESCRIPTION VALUE

Caliper 2.5

REGULATORY APPROVAL

Basis Weight

Prop65 **REACH** RoHS Yes Yes Yes **TPCH CPSIA** UL Yes Yes No

40

Direct Food

No

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448 orders.us@beontag.com

^{*}Please contact your sales representative for details