



Pressure-sensitive adhesives

Acrylic

Film

3.7 MIL SMUDGE KIMDURA / TS523 @ 1.5 Cwt. / 65# C2S L-3

ITEM #84641

| | | |
|--|--------------------------------|---------------------|
| FACESTOCK A 3.7 mil white Smudge Kimdura which is a biaxially oriented three ply polypropylene which combines extraordinary edge tear resistance with a smooth, uniform surface that provides brilliant imagery, superior print quality and smudge resistance. | | |
| Type Film | | |
| Tensile MD 24 Lbs/in | Tensile CD 18 Lbs/in | |
| Tear MD 26 Grams | Tear CD 15 Grams | |
| PROPERTIES | | |
| Caliper | 3.70 Mil | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | FSC No |
| *Please contact your sales representative for details | | |

| | | |
|---|--|--|
| ADHESIVE A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive. | | |
| Type Permanent | Composition Acrylic | Shear 350 |
| Min. Application Temperature 35 F | Min. Service Temperature -65 F | Max. Application Temperature 200 F |
| PROPERTIES | VALUE | |
| Stainless Steel | 5.6 lbs/linear in. | |
| Glass | 2,8lbs/linear in. | |
| Polyethylene | 2.9 | |
| Corrugated | 1.50 lbs./in. | |
| Painted Metal | 4.9 lbs/linear in. | |
| Loop Tack | 2.70 oz/in ² | |

REGULATORY APPROVAL

RoHS
Yes

Prop65
No

REACH
Yes

TPCH
Yes

CPSIA
Yes

Direct Food
No

Indirect Food
Yes

*Please contact your sales representative for details

LINER

A fully bleached kraft liner which has been silicone coated one side to give a controlled release. This paper has high internal strength to withstand all conventional processing operations including, die-cutting, perforating, fanfolding and refolding processes.

Tensile MD
33

Tensile CD
18

Tear MD
51

Tear CD
51

DESCRIPTION

VALUE

Basis Weight

0

Caliper

3,8

REGULATORY APPROVAL

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com