

Pressure-sensitive adhesives

Latex

Film

# 4 MIL FLEXIBLE TC VINYL / AP151 @ 1.3 Cwt. / 65#FBK L-3

### ITEM #978093

### **FACESTOCK**

A 4 mil flexible white vinyl with polymeric plasticizers, formulated to provide optimum performance with pressure sensitive adhesives. The top-coating provides outstanding adhesion to various printing inks.

**Type** Film

 Tensile MD
 Tensile CD

 3900 lb/in
 3800 lb/in

 Tear MD
 Tear CD

 100 Grams
 100 Grams

PROPERTIES VALUE

Caliper 4.0

**REGULATORY APPROVAL** 

RoHSProp65REACHYesYesYes

TPCHCPSIAFSCYesYesNo

## **ADHESIVE**

35 F

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

TypeCompositionShearPermanentLatex80

Min. Application Temperature Min. Service Temperature Max. Application Temperature

-65 F 220 F

PROPERTIES VALUE

**Stainless Steel** 7.3 lbs/linear in.

**Glass** 5.7 lbs/linear in.

Polyethylene 6.5

Corrugated 2.50 lbs./in.

Painted Metal 7.0 lbs/linear in.

**Loop Tack** 5.00 oz/in<sup>2</sup>

<sup>\*</sup>Please contact your sales representative for details

### **REGULATORY APPROVAL**

RoHSProp65REACHYesNoYes

TPCH CPSIA Direct Food

Yes Yes No

**Indirect Food** 

Yes

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448 orders.us@beontag.com