

#55 HIBRIGHT SEMIGLOSS / TP120 @ 1.3 Cwt. / 40#SCK L-3

ITEM #9772

FACESTOCK A premium semigloss calendar coated one side stock with excellent ink receptivity and print characteristics. This stock offers an 88% brightness has an 87% opacity and a 70% gloss rating.		
Type Paper		
Tensile MD 35 Lbs/in	Tensile CD 16 Lbs/in	
Tear MD 35 Grams	Tear CD 38 Grams	
PROPERTIES	VALUE	
Basis Weight	55	
Caliper	2.80 Mil	
Opacity	87	
Brightness	88	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No
*Please contact your sales representative for details		

ADHESIVE A general purpose permanent rubber based adhesive showing high initial tack with high shear and high ultimate adhesion. It has fair plasticizer, UV and solvent resistance. TP120 is not recommended for water immersion. This adhesive has good adhesion to most substrates.		
Type Perm	Composition Latex	
PROPERTIES	VALUE	
Glass	5.7 lbs/linear in.	
Polyethylene	5.1	
REGULATORY APPROVAL		
RoHS	Prop65	REACH

Yes	No	Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No	Indirect Food Yes	FDA 21 CFR 175.105, BfR XIV No
*Please contact your sales representative for details		

ADHESIVE A general purpose permanent rubber based adhesive showing high initial tack with high shear and high ultimate adhesion. It has fair plasticizer, UV and solvent resistance. TP120 is not recommended for water immersion. This adhesive has good adhesion to most substrates.		
Type Permanent	Composition Latex	Shear 0
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 200 F
PROPERTIES	VALUE	
Stainless Steel	5.1 lbs/linear in.	
Glass	2,5lbs/linear in.	
Polyethylene	5.1	
Painted Metal	4.8 lbs/linear in.	
REGULATORY APPROVAL		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		
*Please contact your sales representative for details		

LINER A super calendared kraft paper which has been silicone coated one side to give a controlled release. This paper has a hard, smooth caliper for a consistent surface. Due to it's high internal strength, it will withstand all conventional processing operations including: die-cutting, butt cutting, line scoring, and dispersing.	
Type 5517342 Tensile MD 30 Lbs/In Tear MD 32 Grams	Tensile CD 20 Lbs/In Tear CD 34 Grams
DESCRIPTION	VALUE
Basis Weight	40.5 Lbs/Rm
Caliper	2.5 Mil

REGULATORY APPROVAL

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

UL
No

Direct Food
No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com