

60# EDP / AP151 @ 1.3 Cwt. / 65# C2S L-3

ITEM #151338

| | |
|---|--------------------------------|
| FACESTOCK A white uncoated litho designed with smudge resistance for high speed converting while having excellent perforating, punching and fanfolding characteristics. This stock also offers 88% in brightness and 83% opacity. | |
| Type Paper | |
| Tensile MD 40 Lbs/in | Tensile CD 20 Lbs/in |
| Tear MD 45 Grams | Tear CD 50 Grams |
| PROPERTIES | VALUE |
| Basis Weight | 50 # Rm 25 x 38 |
| Caliper | 3.50 Mil |
| Opacity | 85 |
| Brightness | 88 |
| REGULATORY APPROVAL | |
| Prop65 Yes | FSC No |
| *Please contact your sales representative for details | |

| | | |
|--|--|--|
| ADHESIVE An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits. | | |
| Type Permanent | Composition Latex | Shear 80 |
| Min. Application Temperature 35 F | Min. Service Temperature -65 F | Max. Application Temperature 220 F |
| PROPERTIES | VALUE | |
| Stainless Steel | 7.3 lbs/linear in. | |
| Glass | 5.7 lbs/linear in. | |
| Polyethylene | 6.5 | |
| Corrugated | 2.50 lbs./in. | |
| Painted Metal | 7.0 lbs/linear in. | |

| | | | |
|---|---------------------|--------------------------|-------------------------|
| Loop Tack | | | 5.00 oz/in ² |
| REGULATORY APPROVAL | | | |
| RoHS Yes | Prop65 No | REACH Yes | |
| TPCH Yes | CPSIA Yes | Direct Food No | |
| Indirect Food Yes | | | |
| *Please contact your sales representative for details | | | |

| | | |
|---|-------------------------|---------------------|
| LINER | | |
| A fully bleached kraft liner which has been silicone coated one side to give a controlled release. This paper has high internal strength to withstand all conventional processing operations including, die-cutting, perforating, fanfolding and refolding processes. | | |
| Tensile MD 33 | Tensile CD 18 | |
| Tear MD 51 | Tear CD 51 | |
| | | |
| DESCRIPTION | VALUE | |
| Basis Weight | 0 | |
| Caliper | 3,8 | |
| | | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | |
| *Please contact your sales representative for details | | |

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com