

60# MATTE LITHO / AP151 @ 1.3 Cwt. / 40#SCK L-3

ITEM #77297

| | | |
|--|----------------------------|---------------------|
| FACESTOCK A premium matte litho stock with excellent ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face comes with a brightness of 84% and an opacity of 93%. | | |
| Type Paper | | |
| Tear MD 50 Grams | Tear CD 55 Grams | |
| PROPERTIES | | |
| Basis Weight | 60lbs/3300 sq ft | |
| Caliper | 3.90 Mil | |
| Opacity | 93 | |
| Brightness | 84 | |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 Yes | REACH Yes |
| TPCH Yes | CPSIA Yes | FSC No |
| *Please contact your sales representative for details | | |

| | | |
|--|--|--|
| ADHESIVE An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits. | | |
| Type Permanent | Composition Latex | Shear 80 |
| Min. Application Temperature 35 F | Min. Service Temperature -65 F | Max. Application Temperature 220 F |
| PROPERTIES | VALUE | |
| Stainless Steel | 7.3 lbs/linear in. | |
| Glass | 5.7 lbs/linear in. | |
| Polyethylene | 6.5 | |
| Corrugated | 2.50 lbs./in. | |
| Painted Metal | 7.0 lbs/linear in. | |

| | | |
|---|---------------------|--------------------------|
| Loop Tack | | 5.00 oz/in ² |
| REGULATORY APPROVAL | | |
| RoHS Yes | Prop65 No | REACH Yes |
| TPCH Yes | CPSIA Yes | Direct Food No |
| Indirect Food Yes | | |
| *Please contact your sales representative for details | | |

LINER

A super calendared kraft paper which has been silicone coated one side to give a controlled release. This paper has a hard, smooth caliper for a consistent surface. Due to it's high internal strength, it will withstand all conventional processing operations including: die-cutting, butt cutting, line scoring, and dispersing.

Type

5517342

Tensile MD

30 Lbs/In

Tensile CD

20 Lbs/In

Tear MD

32 Grams

Tear CD

34 Grams

DESCRIPTION

VALUE

Basis Weight

40.5 Lbs/Rm

Caliper

2.5 Mil

REGULATORY APPROVAL

RoHS

Yes

TPCH

Yes

Direct Food

No

Prop65

Yes

CPSIA

Yes

REACH

Yes

UL

No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com