

Pressure-sensitive adhesives

Acrylic

Paper

60# MATTE LITHO / AT333 @ 1.30 Cwt. / 44#PK L-4

ITEM #4705

FACESTOCK

A premium matte litho stock with excellent ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face comes with a brightness of 84% and an opacity of 93%.

Type
Paper

Tear MD Tear CD 50 Grams 55 Grams

PROPERTIES VALUE

Basis Weight 60lbs/3300 sq ft

Caliper 3.90 Mil

93 **Opacity Brightness** 84

REGULATORY APPROVAL

REACH RoHS Prop65 Yes Yes Yes **TPCH CPSIA** FSC Yes Yes No

ADHESIVE

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

Туре	Composition	Shear
Permanent	Acrylic	60

Min. Application Temperature Min. Service Temperature Max. Application Temperature -20 F

-65 F 160 F

PROPERTIES VALUE

Stainless Steel 4.7 lbs/linear in.

Glass 1,3lbs/linear in.

2.2 **Polyethylene**

Corrugated 1.40 lbs./in.

Painted Metal 4.4 lbs/linear in.

^{*}Please contact your sales representative for details

Loop Tack	2.20 oz/in²		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	No	Yes	
TPCH	CPSIA	Direct Food	
Yes	Yes	No No	
Indirect Food Yes	.00	0	
*Please contact your sales rep	presentative for details		

LINER

A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics.

Type 17745

Tensile MD Tensile CD
35 Lbs/ln 13 Lbs/in
Tear MD Tear CD

Tear MDTear CD30 Grams50 Grams

DESCRIPTION VALUE

Caliper 3.1 Mil

REGULATORY APPROVAL

Basis Weight

 RoHS
 Prop65
 REACH

 Yes
 Yes
 Yes

 TPCH
 CPSIA
 UL

 Yes
 No
 No

44 Lbs/Rm

Direct Food

No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448

orders.us@beontag.com