#### Pressure-sensitive adhesives

## Acrylic Paper

# 60# ULTRA WHITE SemiGloss / AT333 @ 1.30 Cwt. / 40#SCK L-2 TU

ITEM #9969227

## FACESTOCK

A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 90% Brightness and an 88% opacity.

Туре			
Paper			
Tensile MD	Tensile CD		
35 Lbs/in	19 Lbs/in		
Tear MD	Tear CD		
47 Grams	46 Grams		
PROPERTIES	VALUE		
Basis Weight	60 # Rm 25 x 38		
Caliper	3.20 Mil		
Opacity	88		
Brightness	90		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	FSC	
Yes	Yes	No	

## **ADHESIVE**

An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.

<b>Type</b> Permanent	Composition Acrylic	Shear 60
<b>Min. Application Temperature</b> -20 F	<b>Min. Service Temperature</b> -65 F	<b>Max. Application Temperature</b> 160 F
PROPERTIES	VALUE	
Stainless Steel	4.7 lbs/linear in.	
Glass	1,3lbs/linear in.	
Polyethylene	2.2	
Corrugated	1.40 lbs./in.	

Painted Metal Loop Tack	4.4 lbs/linear in. 2.20 oz/in²		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	No	Yes	
ТРСН	CPSIA	Direct Food	
Yes	Yes	No	
<b>Indirect Food</b> Yes			
*Please contact your sales re	epresentative for details		

## LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

<b>Tensile MD</b> 34	<b>Tensile CD</b> 22			
<b>Tear MD</b> 32	<b>Tear CD</b> 34			
DESCRIPTION	VALUE			
Basis Weight	40			
Caliper	2,5			
REGULATORY APPROVAL				
RoHS Yes	Prop65 Yes	<b>REACH</b> Yes		
<b>трсн</b> Yes	<b>CPSIA</b> Yes			
*Please contact your sales representative for details				

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS: Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 <u>800-358-4448</u> <u>orders.us@beontag.com</u>