

60# Ultra White Semigloss / TP170 @ 1.3 Cwt. / 40#SCK L-3

ITEM #78179

FACESTOCK

A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 90% Brightness and an 88% opacity.

Type

Paper

Tensile MD

35 Lbs/in

Tensile CD

19 Lbs/in

Tear MD

47 Grams

Tear CD

46 Grams

PROPERTIES

VALUE

Basis Weight

60 # Rm 25 x 38

Caliper

3.20 Mil

Opacity

88

Brightness

90

REGULATORY APPROVAL

RoHS

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

FSC

No

*Please contact your sales representative for details

ADHESIVE

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Type

Permanent

Composition

Acrylic

Shear

300

Min. Application Temperature

35 F

Min. Service Temperature

-65 F

Max. Application Temperature

180 F

PROPERTIES

VALUE

Stainless Steel

5.2 lbs/linear in.

Glass

3,2lbs/linear in.

Polyethylene

1.6

Corrugated

1.40 lbs./in.

| | |
|---|--------------------------|
| Painted Metal | 5.2 lbs/linear in. |
| Loop Tack | 2.20 oz/in ² |
| REGULATORY APPROVAL | |
| RoHS Yes | Prop65 No |
| TPCH Yes | CPSIA Yes |
| Indirect Food Yes | REACH Yes |
| | Direct Food No |
| *Please contact your sales representative for details | |

| | |
|---|--------------------------------|
| LINER | |
| A super calendared kraft paper which has been silicone coated one side to give a controlled release. This paper has a hard, smooth caliper for a consistent surface. Due to it's high internal strength, it will withstand all conventional processing operations including: die-cutting, butt cutting, line scoring, and dispersing. | |
| Type 5517342 | |
| Tensile MD 30 Lbs/In | Tensile CD 20 Lbs/In |
| Tear MD 32 Grams | Tear CD 34 Grams |
| DESCRIPTION | VALUE |
| Basis Weight | 40.5 Lbs/Rm |
| Caliper | 2.5 Mil |
| REGULATORY APPROVAL | |
| RoHS Yes | Prop65 Yes |
| TPCH Yes | CPSIA Yes |
| Direct Food No | REACH Yes |
| | UL No |
| *Please contact your sales representative for details | |

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com