

60# ULTRA WHITE SemiGloss / TS523A / 40#SCK L-3

ITEM #79706

FACESTOCK A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 90% Brightness and an 88% opacity.		
Type Paper		
Tensile MD 35 Lbs/in	Tensile CD 19 Lbs/in	
Tear MD 47 Grams	Tear CD 46 Grams	
PROPERTIES		
Basis Weight	60 # Rm 25 x 38	
Caliper	3.20 Mil	
Opacity	88	
Brightness	90	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No
*Please contact your sales representative for details		

ADHESIVE A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.		
Type Permanent	Composition Acrylic	Shear 300
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 180 F
PROPERTIES	VALUE	
Stainless Steel	5.2 lbs/linear in.	
Glass	2,8lbs/linear in.	
Polyethylene	2.9	
Corrugated	1.40 lbs./in.	
Painted Metal		

5.2 lbs/linear in.

Loop Tack

2.20 oz/in²

REGULATORY APPROVAL

RoHS
Yes

Prop65
No

REACH
Yes

TPCH
Yes

CPSIA
Yes

Direct Food
No

Indirect Food
Yes

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type
5517342

Tensile MD
34

Tensile CD
22

Tear MD
32

Tear CD
34

DESCRIPTION

VALUE

Basis Weight

40

Caliper

2.5

REGULATORY APPROVAL

RoHS
Yes

Prop65
Yes

REACH
Yes

TPCH
Yes

CPSIA
Yes

UL
No

Direct Food
No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com