

# 60# ULTRA WHITE SemiGloss / TS583 @ 2.10 Cwt. / 40#SCK L-3



ITEM #78178

## Facestock

A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 90% Brightness and an 88% opacity.

### Type

Paper

### Tensile MD

35 Lbs/in

### Tensile CD

19 Lbs/in

### Tear MD

47 Grams

### Tear CD

46 Grams

### Properties

### Value

### Caliper

3.20 Mil

### Opacity

88

### Brightness

90

## Regulatory Approval

### RoHS

Yes

### Prop65

Yes

### REACH

Yes

### TPCH

Yes

### CPSIA

Yes

### FSC

Yes

\*Please contact your sales representative for details

## Adhesive

A specialty adhesive designed to adhere to hard to label surfaces with excellent ultimate adhesion when applied at temperatures as low as -20 F. Outstanding permanency at room temperatures. This adhesive has good plasticizer, UV & solvent resistance and high initial tack.

### Type

Permanent

### Composition

Acrylic

### Shear

70

### Min. Application Temperature

-20 F

### Min. Service Temperature

-65 F

### Max. Application Temperature

160 F

### Properties

### Value

<b>Stainless Steel</b>	5.9 lbs/linear in.
<b>Glass</b>	4.2
<b>Polyethylene</b>	4.1
<b>Corrugated</b>	1.50 lbs./in.
<b>Painted Metal</b>	5.1 lbs/linear in.
<b>Loop Tack</b>	3.20 lbs./in <sup>2</sup>

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> No	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No	<b>Indirect Food</b> Yes	

\*Please contact your sales representative for details

### Liner

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

#### Type

5517342

#### Tensile MD

34 Lbs/In

#### Tensile CD

22 Lbs/In

#### Tear MD

32 Grams

#### Tear CD

34 Grams

#### Description

#### Value

#### Basis Weight

40 Lbs/Rm

#### Caliper

2.5 Mil

### Regulatory Approval

<b>RoHS</b> Yes	<b>Prop65</b> Yes	<b>REACH</b> Yes
<b>TPCH</b> Yes	<b>CPSIA</b> Yes	<b>UL</b> No
<b>Direct Food</b> No		

\*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag

6206 Wolf Creek Pike

Trotwood, OH 45426

[800-358-4448](tel:800-358-4448)

[orders.us@beontag.com](mailto:orders.us@beontag.com)