

#8 ESTATE WHITE VELLUM / IP400 @ 1.7 Cwt. / 44#PK L-4

ITEM #78904

|   |                                |                     |
|---|--------------------------------|---------------------|
| <b>FACESTOCK</b><br>Estate label is an uncoated, wet strength grade, face stock which meets the demanding packaging needs of the wine industry. The estate label combines prestige appearance with sophisticated production properties that ensure smooth performance on many high speed presses. |                                |                     |
| <b>Type</b><br>Paper  |                                |                     |
| <b>Tensile MD</b><br>30 Lbs/in  | <b>Tensile CD</b><br>16 Lbs/in |                     |
| <b>Tear MD</b><br>50  | <b>Tear CD</b><br>55           |                     |
| <b>PROPERTIES</b>   |                                |                     |
| <b>Basis Weight</b>   | 60 # Rm 25 x 38                |                     |
| <b>Caliper</b>  | 5.30 Mil                       |                     |
| <b>Opacity</b>  | 93                             |                     |
| <b>REGULATORY APPROVAL</b>  |                                |                     |
| <b>RoHS</b><br>Yes  | <b>Prop65</b><br>Yes           | <b>REACH</b><br>Yes |
| <b>TPCH</b><br>Yes  | <b>CPSIA</b><br>Yes            | <b>UL</b><br>No     |
| <b>FSC</b><br>No  |                                |                     |
| *Please contact your sales representative for details   |                                |                     |

|   |  |  |
|---|--|--|
| <b>ADHESIVE</b><br>A specialty adhesive designed to adhere to glass wine bottles with good ultimate adhesion when applied at temperatures as low as +35 F. Excellent permanency at room temperatures. Good plasticizer, UV & solvent resistance. Excellent adhesive for wet strength wine label facestocks when submersed in ice buckets. |  |  |
| <b>Type</b><br>Permanent  | <b>Composition</b><br>Acrylic            | <b>Shear</b><br>80                           |
| <b>Min. Application Temperature</b><br>35 F   | <b>Min. Service Temperature</b><br>-65 F | <b>Max. Application Temperature</b><br>200 F |
| <b>PROPERTIES</b>   | <b>VALUE</b>                             |  |
| <b>Stainless Steel</b>  | 5.5 lbs/linear in.                       |  |
| <b>Glass</b>  | 3,2lbs/linear in.                        |  |
| <b>Polyethylene</b>   | 2  |  |

|   |                         |                          |
|---|-------------------------|--------------------------|
| <b>Corrugated</b>                                     | 1.45 lbs./in.           |                          |
| <b>Painted Metal</b>                                  | 3.0 lbs/linear in.      |                          |
| <b>Loop Tack</b>                                      | 5.00 oz/in <sup>2</sup> |                          |
| <b>REGULATORY APPROVAL</b>                            |                         |                          |
| <b>RoHS</b><br>Yes                                    | <b>Prop65</b><br>Yes    | <b>REACH</b><br>Yes      |
| <b>TPCH</b><br>Yes                                    | <b>CPSIA</b><br>Yes     | <b>Direct Food</b><br>No |
| <b>Indirect Food</b><br>Yes                           |                         |                          |
| *Please contact your sales representative for details |                         |                          |

|   |                                |                     |
|---|--------------------------------|---------------------|
| <b>LINER</b>  |                                |                     |
| A medium weight natural kraft coated 1 side (C1S) with a gloss polyethylene. Silicone coating has been added on the gloss side (C1S) for a controlled release. It has superb smoothness, excellent dimensional stability and exceptional layflat characteristics. |                                |                     |
| <b>Type</b><br>17745  |                                |                     |
| <b>Tensile MD</b><br>35 Lbs/In  | <b>Tensile CD</b><br>13 Lbs/in |                     |
| <b>Tear MD</b><br>30 Grams  | <b>Tear CD</b><br>50 Grams     |                     |
| <b>DESCRIPTION</b>  |                                |                     |
| <b>VALUE</b>  |                                |                     |
| <b>Basis Weight</b>   | 44 Lbs/Rm                      |                     |
| <b>Caliper</b>  | 3.1 Mil                        |                     |
| <b>REGULATORY APPROVAL</b>  |                                |                     |
| <b>RoHS</b><br>Yes  | <b>Prop65</b><br>Yes           | <b>REACH</b><br>Yes |
| <b>TPCH</b><br>Yes  | <b>CPSIA</b><br>Yes            | <b>UL</b><br>No     |
| <b>Direct Food</b><br>No  |                                |                     |
| *Please contact your sales representative for details   |                                |                     |

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:  
Beontag  
6206 Wolf Creek Pike  
Trotwood, OH 45426  
[800-358-4448](tel:800-358-4448)

