

BRIGHT WHITE EDP / AP151 @ 1.3 Cwt. / 50#SCK L-3

ITEM #4407289

FACESTOCK A white uncoated litho designed with smudge resistance for high speed converting while having excellent perforating, punching and fanfolding characteristics. This stock also offers 88% in brightness and 83% opacity.	
Type Paper	
Tensile MD 40 Lbs/in	Tensile CD 20 Lbs/in
Tear MD 45 Grams	Tear CD 50 Grams
PROPERTIES	VALUE
Basis Weight	50 # Rm 25 x 38
Caliper	3.50 Mil
Opacity	85
Brightness	88
REGULATORY APPROVAL	
Prop65 Yes	FSC No
*Please contact your sales representative for details	

ADHESIVE An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.		
Type Permanent	Composition Latex	Shear 80
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 220 F
PROPERTIES	VALUE	
Stainless Steel	7.3 lbs/linear in.	
Glass	5.7 lbs/linear in.	
Polyethylene	6.5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	

Loop Tack			5.00 oz/in ²
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	No	Yes	
TPCH	CPSIA	Direct Food	
Yes	Yes	No	
Indirect Food			
Yes			
*Please contact your sales representative for details			

LINER		
Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.		
Type 5517353		
Tensile MD 40	Tensile CD 24	
Tear MD 44	Tear CD 48	
DESCRIPTION		
Basis Weight	50	
Caliper	3.2	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		
*Please contact your sales representative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448
orders.us@beontag.com