

CHARTREUSE FLUORESCENT / AP151 @ 1.3 Cwt. / 40#SCK L-5

ITEM #151027

FACESTOCK A premium coated one side face stock in a bright fluorescent color with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting.		
Type Paper		
Tensile MD 26 Lbs/in	Tensile CD 14 Lbs/in	
Tear MD 45 Grams	Tear CD 53 Grams	
PROPERTIES		
Basis Weight	54 # Rm 25 x 38	
Caliper	3.80 Mil	
Opacity	0	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No
*Please contact your sales representative for details		

ADHESIVE An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.		
Type Permanent	Composition Latex	Shear 80
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 220 F
PROPERTIES	VALUE	
Stainless Steel	7.3 lbs/linear in.	
Glass	5.7 lbs/linear in.	
Polyethylene	6.5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	

Loop Tack			5.00 oz/in ²
REGULATORY APPROVAL			
RoHS Yes	Prop65 No	REACH Yes	
TPCH Yes	CPSIA Yes	Direct Food No	
Indirect Food Yes			
*Please contact your sales representative for details			

LINER			
Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.			
Tensile MD 34		Tensile CD 22	
Tear MD 32		Tear CD 34	
DESCRIPTION		VALUE	
Basis Weight		40	
Caliper		2,5	
REGULATORY APPROVAL			
RoHS Yes		Prop65 Yes	REACH Yes
TPCH Yes		CPSIA Yes	
*Please contact your sales representative for details			

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com