

Pressure-sensitive adhesives

Acrylic

Paper

# Dull Gold Laminated Foil / TS523 @ 1.5 Cwt. / 50#SCK L-3

#### ITEM #1013

F	ΞΔ	CF	SI	n	C	K

A 60# acrylic topcoated foil paper that accepts water base and solvent base inks and can be embossed.

Туре Paper

**Tensile MD** 

**Tensile CD** 36 Lbs/in 23 Lbs/in **Tear MD Tear CD** 50 Grams 51 Grams

**PROPERTIES** 

**Basis Weight** 60 # Rm 25 x 38

Caliper 3.60 Mil

**REGULATORY APPROVAL** 

**REACH RoHS** Prop65 Yes Yes Yes **TPCH CPSIA FSC** Yes Yes No

**VALUE** 

## **ADHESIVE**

A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.

Type Composition Shear Permanent Acrylic 350

Min. Service Temperature Min. Application Temperature Max. Application Temperature

35 F -65 F 200 F

**PROPERTIES VALUE** 

Stainless Steel 5.6 lbs/linear in. **Glass** 2,8lbs/linear in.

**Polyethylene** 2.9

1.50 lbs./in. Corrugated

**Painted Metal** 4.9 lbs/linear in.

2.70 oz/in<sup>2</sup> **Loop Tack** 

<sup>\*</sup>Please contact your sales representative for details

## **REGULATORY APPROVAL**

RoHSProp65REACHYesNoYes

TPCH CPSIA Direct Food

Yes Yes No

#### **Indirect Food**

Yes

\*Please contact your sales representative for details

#### **LINER**

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

# Туре

5517353

Tensile MD Tensile CD

40 2

 Tear MD
 Tear CD

 44
 48

DESCRIPTION		VALUE

Basis Weight 50
Caliper 3.2

# **REGULATORY APPROVAL**

 RoHS
 Prop65
 REACH

 Yes
 Yes
 Yes

 TPCH
 CPSIA
 UL

 Yes
 No
 No

#### **Direct Food**

No

\*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 800-358-4448

orders.us@beontag.com