



Pressure-sensitive adhesives

Acrylic

Film

EARTHFIRST 2 MIL PLA CLEAR FILM / TS523 @ 1.5 Cwt. / 40#SCK L-3

ITEM #81933

FACESTOCK An environmentally friendly clear film made from 100% annually renewable resource corn. 100% compostable. This product features high gloss, optimum clarity and transparency, as well as excellent printability. 2 mil PLA is a breathable film, with great fiber tear, excellent optical properties and outstanding twist retention.		
Type Film		
Tensile MD 14000 Psi	Tensile CD 26000 Psi	
PROPERTIES		
Caliper	2.00 Mil	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	FSC No
*Please contact your sales representative for details		

ADHESIVE A tri-bonded specialty clear acrylic adhesive featuring high initial tack, high shear & high ultimate adhesion with excellent clarity and minimum cold flow. It has outstanding plasticizer, UV, solvent and occasional water and oil resistance. This is an acid free adhesive.		
Type Permanent	Composition Acrylic	Shear 350
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 200 F
PROPERTIES		
Stainless Steel	5.6 lbs/linear in.	
Glass	2,8lbs/linear in.	
Polyethylene	2.9	
Corrugated	1.50 lbs./in.	
Painted Metal	4.9 lbs/linear in.	
Loop Tack	2.70 oz/in ²	
REGULATORY APPROVAL		

RoHS

Yes

Prop65

No

REACH

Yes

TPCH

Yes

CPSIA

Yes

Direct Food

No

Indirect Food

Yes

*Please contact your sales representative for details

LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Type

5517342

Tensile MD

34

Tensile CD

22

Tear MD

32

Tear CD

34

DESCRIPTION**VALUE****Basis Weight**

40

Caliper

2.5

REGULATORY APPROVAL**RoHS**

Yes

Prop65

Yes

REACH

Yes

TPCH

Yes

CPSIA

Yes

UL

No

Direct Food

No

*Please contact your sales representative for details

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com