



Pressure-sensitive adhesives

Latex

FREE-FILM 40#SCK AP151 40#SCK

ITEM #89042

ADHESIVE An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.		
Type Permanent	Composition Latex	Shear 80
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 220 F
PROPERTIES	VALUE	
Stainless Steel	7.3 lbs/linear in.	
Glass	5.7 lbs/linear in.	
Polyethylene	6.5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	
Loop Tack	5.00 oz/in²	
REGULATORY APPROVAL		
RoHS Yes	Prop65 No	REACH Yes
TPCH Yes	CPSIA Yes	Direct Food No
Indirect Food Yes		
*Please contact your sales representative for details		

LINER A super calendered kraft paper which has been silicone coated one side to give a controlled release. This paper has a hard, smooth caliper for a consistent surface. Due to it's high internal strength, it will withstand all conventional processing operations including: die-cutting, butt cutting, line scoring, and dispersing.	
Type 5517342	
Tensile MD 30 Lbs/In	Tensile CD 20 Lbs/In
Tear MD 32 Grams	Tear CD 34 Grams
DESCRIPTION	VALUE

Basis Weight	40.5 Lbs/Rm		
Caliper	2.5 Mil		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
TPCH	CPSIA	UL	
Yes	Yes	No	
Direct Food			
No			
*Please contact your sales representative for details			

Last update: 08/19/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products.

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com