

Pressure-sensitive adhesives Acrylic

Acrylic

RADIANT WHITE LASER / TP170 @ 1.3 Cwt. / 2.5 MIL LAYFLAT L-3

ITEM #89676

FACESTOCK		
Туре		
Paper		
Tensile MD	Tensile CD	
34 Lbs/in	22 Lbs/in	
Tear MD	Tear CD	
50 Grams	56 Grams	
PROPERTIES	VALUE	
Basis Weight	56lbs/3300 sq ft	
Caliper	4.00 Mil	
Opacity	89	
Brightness	94	
REGULATORY APPROVAL		
Prop65	FSC	
Yes	No	

ADHESIVE

A general purpose acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Type Permanent	Composition Acrylic	Shear 300
Min. Application Temperature 35 F	Min. Service Temperature -65 F	Max. Application Temperature 180 F
PROPERTIES	VALUE	
Stainless Steel	5.2 lbs/linear in.	
Glass	3,2lbs/linear in.	
Polyethylene	1.6	
Corrugated	1.40 lbs./in.	
Painted Metal	5.2 lbs/linear in.	
Loop Tack	2.20 oz/in ²	

REGULATORY APPROVAL

RoHS Prop65 **REACH** No Yes Yes

CPSIA **TPCH Direct Food** No

Yes Yes

Indirect Food

Yes

35 F

ADHESIVE

A general purpose patterned acrylic adhesive showing good initial tack with high shear and high ultimate adhesion. It has good plasticizer, UV and solvent resistance. This adhesive displays excellent die-cutting and stripping characteristics and has good adhesion to many different substrates.

Composition Shear Туре Permanent Acrylic

Min. Application Temperature Min. Service Temperature Max. Application Temperature

-65 F

PROPERTIES	VALUE	
Stainless Steel	5.2 lbs/linear in.	
Glass	3,2lbs/linear in.	
Polyethylene	1.6	
Painted Metal	5.2 lbs/linear in.	

180 F

REGULATORY APPROVAL

RoHS Prop65 **REACH** Yes No Yes

TPCH CPSIA Direct Food

Yes Yes No

Indirect Food

Yes

LINER

A bleached kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand die-cutting and has excellent layflat characteristics while providing outstanding dimensional stability.

Type 901967

Tensile MD Tensile CD

24 10

Tear CD **Tear MD** 28 32

DESCRIPTION VALUE

Basis Weight

^{*}Please contact your sales representative for details

^{*}Please contact your sales representative for details

40 O. France	0.5	
Caliper	2.5	
REGULATORY APPROVAL		
RoHS Yes	Prop65 Yes	REACH Yes
TPCH Yes	CPSIA Yes	UL No
Direct Food No		

Last update: 05/01/2024

*Please contact your sales representative for details

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
800-358-4448

orders.us@beontag.com