



Pressure-sensitive adhesives

Acrylic

Acrylic

Paper

RADIANT WHITE LASER W / 1 MIL BARRIER / AT333 HCWT / 3.4 MIL LAYFLAT L-3

ITEM #69552

FACESTOCK	
Type Paper	
Tensile MD 34 Lbs/in	Tensile CD 22 Lbs/in
Tear MD 50 Grams	Tear CD 56 Grams
PROPERTIES	VALUE
Basis Weight	56lbs/3300 sq ft
Caliper	4.00 Mil
Opacity	89
Brightness	94
REGULATORY APPROVAL	
Prop65 Yes	FSC No
*Please contact your sales representative for details	

ADHESIVE		
An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.		
Type Permanent	Composition Acrylic	Shear 60
Min. Application Temperature -20 F	Min. Service Temperature -65 F	Max. Application Temperature 160 F
PROPERTIES	VALUE	
Stainless Steel	4.9 lbs/linear in.	
Glass	1.3 lbs/linear in.	
Polyethylene	2.2	
Corrugated	1.50 lbs./in.	
Painted Metal	4.7 lbs/linear in.	

Loop Tack

2.40 oz/in²

REGULATORY APPROVAL

RoHS

Yes

TPCH

Yes

Indirect Food

Yes

Prop65

No

CPSIA

Yes

REACH

Yes

Direct Food

No

*Please contact your sales representative for details

*Please contact your sales representative for details

<div>ADHESIVE</div> <div>An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps.</div>		
<div>Type</div> <div>Permanent</div>	<div>Composition</div> <div>Acrylic</div>	<div>Shear</div> <div>60</div>
<div>Min. Application Temperature</div> <div>-20 F</div>	<div>Min. Service Temperature</div> <div>-65 F</div>	<div>Max. Application Temperature</div> <div>160 F</div>
<div>PROPERTIES</div>	<div>VALUE</div>	
<div>Stainless Steel</div>	<div>4.7 lbs/linear in.</div>	
<div>Glass</div>	<div>1,3lbs/linear in.</div>	
<div>Polyethylene</div>	<div>2.2</div>	
<div>Corrugated</div>	<div>1.40 lbs./in.</div>	
<div>Painted Metal</div>	<div>4.4 lbs/linear in.</div>	
<div>Loop Tack</div>	<div>2.20 oz/in²</div>	
<div>REGULATORY APPROVAL</div>		
<div>RoHS</div> <div>Yes</div>	<div>Prop65</div> <div>No</div>	<div>REACH</div> <div>Yes</div>
<div>TPCH</div> <div>Yes</div>	<div>CPSIA</div> <div>Yes</div>	<div>Direct Food</div> <div>No</div>
<div>Indirect Food</div> <div>Yes</div>		
<div>*Please contact your sales representative for details</div>		

*Please contact your sales representative for details

<div> <div>LINER</div> <div> A bleached kraft liner which has been silicone coated one side to give a controlled release. It is designed to withstand die-cutting, marginal punching, perforating, fanfolding and refolding process while providing excellent dimensional stability. </div> </div>	
<div> <div>Type</div> <div>517391</div> </div>	
<div> <div>Tensile MD</div> <div>35</div> </div>	<div> <div>Tensile CD</div> <div>15</div> </div>
<div> <div>Tear MD</div> </div>	<div> <div>Tear CD</div> </div>

50	75	
DESCRIPTION	VALUE	
Basis Weight	47	
Caliper	3.4	
REGULATORY APPROVAL		
RoHS	Prop65	REACH
Yes	Yes	Yes
TPCH	CPSIA	UL
Yes	Yes	No
Direct Food		
No		
*Please contact your sales representative for details		

Last update: 08/20/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:
Beontag
6206 Wolf Creek Pike
Trotwood, OH 45426
[800-358-4448](tel:800-358-4448)
orders.us@beontag.com