Pressure-sensitive adhesives

Paper

Latex

## RECYCLED SemiGloss / AP151 @ 1.3 Cwt. / 40#SCK L-3

ITEM #151035

## FACESTOCK

A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 89% brightness and an 92% opacity.

<b>Type</b> Paper				
PROPERTIES	VALUE			
Basis Weight	80 # Rm 25 x 38			
Caliper	4.20 Mil 93			
Opacity				
Brightness	83			
REGULATORY APPROVAL				
RoHS	Prop65	REACH		
Yes	Yes	Yes		
ТРСН	CPSIA	FSC		
Yes	Yes	No		
*Please contact your sales rep	presentative for details			

## ADHESIVE

An improved general purpose permanent rubber based adhesive which has high initial tack and high ultimate adhesion. It is recommended for high speed wide web processing and can be used on many different substrates. Displays excellent die-cutting & stripping traits.

<b>Type</b> Permanent	<b>Composition</b> Latex	<b>Shear</b> 80
<b>Min. Application Temperature</b> 35 F	<b>Min. Service Temperature</b> -65 F	<b>Max. Application Temperature</b> 220 F
PROPERTIES	VALUE	
Stainless Steel	7.3 lbs/linear in.	
Glass	5.7 lbs/linear in.	
Polyethylene	6.5	
Corrugated	2.50 lbs./in.	
Painted Metal	7.0 lbs/linear in.	
Loop Tack	5.00 oz/in²	

REGULATORY APPROVAL				
<b>RoHS</b> Yes	Prop65 No	<b>REACH</b> Yes		
		Direct Food		
ТРСН	CPSIA	Direct Food		
TPCH Yes Indirect Food	Yes	No		

\*Please contact your sales representative for details

## LINER

Supercalendered Kraft (SCK) liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper consistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

<b>Туре</b> 5517342			
	7 1 00		
Tensile MD	Tensile CD		
34	22		
Tear MD	Tear CD		
32	34		
DESCRIPTION	VALUE		
Basis Weight	40		
Caliper	2.5		
REGULATORY APPROVAL			
RoHS	Prop65	REACH	
Yes	Yes	Yes	
ТРСН	CPSIA	UL	
Yes	Yes	No	
<b>Direct Food</b> No			
*Please contact your sales repr	esentative for details		

Last update: 05/01/2024

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG's standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

ADDRESS:

Beontag 6206 Wolf Creek Pike Trotwood, OH 45426 <u>800-358-4448</u> <u>orders.us@beontag.com</u>