



Pressure-sensitive adhesives

Acrylic

Paper

RECYCLED SemiGloss / AT333 @ 1.30 Cwt. / 40#SCK L-3

ITEM #91955

|  |                      |                     |  |
|--|----------------------|---------------------|--|
| <b>FACESTOCK</b><br>A premium coated one side stock with outstanding ink receptivity and print characteristics. It also offers good flexibility and high internal strength for ease in converting. This face offers a 89% brightness and an 92% opacity. |                      |                     |  |
| <b>Type</b><br>Paper   |                      |                     |  |
| <b>PROPERTIES</b>  |                      | <b>VALUE</b>        |  |
| <b>Basis Weight</b>  |                      | 80 # Rm 25 x 38     |  |
| <b>Caliper</b>   |                      | 4.20 Mil            |  |
| <b>Opacity</b>   |                      | 93                  |  |
| <b>Brightness</b>  |                      | 83                  |  |
| <b>REGULATORY APPROVAL</b>   |                      |                     |  |
| <b>RoHS</b><br>Yes   | <b>Prop65</b><br>Yes | <b>REACH</b><br>Yes |  |
| <b>TPCH</b><br>Yes   | <b>CPSIA</b><br>Yes  | <b>FSC</b><br>No    |  |
| *Please contact your sales representative for details  |                      |                     |  |

|   |  |  |
|---|--|--|
| <b>ADHESIVE</b><br>An all temperature and freezer grade acrylic adhesive with good initial tack and high ultimate adhesion when applied at temperatures as low as -20 F. Very good plasticizer, UV and solvent resistance. AT333 adhesive allows for short term reposition on many substrates, yet displays excellent permanency at room temps. |  |  |
| <b>Type</b><br>Permanent  | <b>Composition</b><br>Acrylic            | <b>Shear</b><br>60                           |
| <b>Min. Application Temperature</b><br>-20 F  | <b>Min. Service Temperature</b><br>-65 F | <b>Max. Application Temperature</b><br>160 F |
| <b>PROPERTIES</b>   | <b>VALUE</b>                             |  |
| <b>Stainless Steel</b>  | 4.7 lbs/linear in.                       |  |
| <b>Glass</b>  | 1,3lbs/linear in.                        |  |
| <b>Polyethylene</b>   | 2.2                                      |  |
| <b>Corrugated</b>   | 1.40 lbs./in.                            |  |
| <b>Painted Metal</b>  | 4.4 lbs/linear in.                       |  |
| <b>Loop Tack</b>  | 2.20 oz/in <sup>2</sup>                  |  |

**REGULATORY APPROVAL**

**RoHS**  
Yes

**Prop65**  
No

**REACH**  
Yes

**TPCH**  
Yes

**CPSIA**  
Yes

**Direct Food**  
No

**Indirect Food**  
Yes

\*Please contact your sales representative for details

**LINER**

A super calendared kraft paper which has been silicone coated one side to give a controlled release. This paper has a hard, smooth caliper for a consistent surface. Due to it's high internal strength, it will withstand all conventional processing operations including: die-cutting, butt cutting, line scoring, and dispersing.

**Type**  
5517342

**Tensile MD**  
30 Lbs/In

**Tensile CD**  
20 Lbs/In

**Tear MD**  
32 Grams

**Tear CD**  
34 Grams

**DESCRIPTION**

**VALUE**

**Basis Weight**

40.5 Lbs/Rm

**Caliper**

2.5 Mil

**REGULATORY APPROVAL**

**RoHS**  
Yes

**Prop65**  
Yes

**REACH**  
Yes

**TPCH**  
Yes

**CPSIA**  
Yes

**UL**  
No

**Direct Food**  
No

\*Please contact your sales representative for details

Last update: 05/01/2024

**WARRANTY:** All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. BEONTAG will not be liable for damages in excess of the purchase price of Products or for incidental or consequential damages.

BEONTAG warrants the products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year after the initial date of shipment (unless otherwise stated), BEONTAG shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with BEONTAG'S standards, correct such defects by suitable repair or replacement without charge at BEONTAG's plant or at the location of the products (at BEONTAG's election); provided, however, if BEONTAG determines that repair or replacement is not commercially practical, BEONTAG shall issue a credit in favor of BUYER in an amount not to exceed the purchase price of the products

**ADDRESS:**

Beontag  
6206 Wolf Creek Pike  
Trotwood, OH 45426  
[800-358-4448](tel:800-358-4448)  
[orders.us@beontag.com](mailto:orders.us@beontag.com)